



TC-5389

ELECTRICAL RESEARCH AND DEVELOPMENT ASSOCIATION

(Accredited by the National Accreditation Board for Testing and Calibration Laboratories, Govt. of India)

ERDA Road, Makarpura Industrial Estate, Vadodara-390 010, India.

EPABX : +91 (0265) 2642942, 2642964, 2642377, 3043128 / 29 / 30 / 31 / 33

Fax : +91 (0265) 2638382

E-mail : erda@erda.org

Web : http://www.erda.org



RP-2324-036777

TEST REPORT

ULR No.: TC538924000006930F

SHEET 1 of 4

NAME AND ADDRESS OF CUSTOMERSavita Oil Technologies Limited.
17/17A, Thane Belapur Road,
PO Turbhe, Vashi,
Navi Mumbai.**REPORT No**

RP-2324-036777

DATE OF ISSUE

23/03/2024

**CUSTOMER REF. No
DATED**Letter
05/12/2023**DATE OF SAMPLE
RECEIPT**

07/12/2023

DATES OF TESTING

12/03/2024 to 21/03/2024

SAMPLE DESCRIPTION(As provided by customer)
Unused Synthetic Ester oil.
Make : M/s Savita Oil Technologies Ltd.,
TRANSOL synth. 100
Quantity of sample: 3 Litres. (3 Nos. x 1 litre in each bottle)**SAMPLE IDENTIFICATION**ERDA Sample Code No.:
ERDA-00555937**TEST DETAILS**

Test details on sheet 1 of 4

TEST SPECIFICATION

IEC : 61099 -2010

Note : Separate test report No. RP-2324-036778 dtd. 23/03/2024 is issued for the non - accredited tests for the testing carried out for ERDA Sample code No. ERDA-00555937 submitted to ERDA.**Remarks :** 1. The sample conforms to the requirement for the mentioned tests.
2. Photo of sample bottles in as received condition is provided on sheet 4 of 4.**CHECKED BY****NOTE:**

1. This report relates only to the particular sample received for testing in good condition at ERDA, Vadodara
2. This report cannot be reproduced in part under any circumstances.
3. Publication of this report requires prior permission in writing from Director, ERDA.
4. This report shall not be used for any purpose such as PR brochures, propaganda, advertisement and/or legal proceedings, unless for the granted purpose.
5. Only the tests asked for by the customer have been carried out.
6. Particulars of manufacturer/supplier, given in this report are based on information supplied by the customer, along with the test request/sample. ERDA does not assume any responsibility for the correctness of the information for above mentioned Sample under test (SUT). ERDA will not be responsible for any changes in SUT made after the test. This test report is given as per instrument status while testing.
7. In case of any dispute, Vadodara will be the exclusive jurisdiction & shall be construed as where the cause has arisen.

Caution:ERDA is not responsible for the authenticity of photocopied or reproduced test reports.
ERDA provides support to customers for verification of the authenticity of test reports issued by ERDA within 10 years of date of issue of report.(Mr. J.P.SHETH)
APPROVED BY

TC 3545209



TC-5389

ELECTRICAL RESEARCH AND DEVELOPMENT ASSOCIATION

(Accredited by the National Accreditation Board for Testing and Calibration Laboratories, Govt. of India)

ERDA Road, Makarpura Industrial Estate, Vadodra-390 010, India.

EPABX : +91 (0265) 2642942, 2642964, 2642377, 3043128 / 29 / 30 / 31 / 33

Fax : +91 (0265) 2638382

E-mail : erda@erda.org

Web : http://www.erda.org



ULR No.: TC538924000006930F

TEST REPORT No: RP-2324-036777

DATE OF ISSUE: 23/03/2024

SHEET 2 of 4

Sr. No.	TEST DETAILS:	TEST SPECIFICATION:
---------	---------------	---------------------

Physical

- | | | |
|----|---------------------|-------------------|
| 1. | Appearance | IEC : 61099 -2010 |
| 2. | Density | IEC : 61099 -2010 |
| 3. | Kinematic Viscosity | IEC : 61099 -2010 |
| 4. | Flash Point | IEC : 61099 -2010 |
| 5. | Fire Point | IEC : 61099 -2010 |
| 6. | Pour Point | IEC : 61099 -2010 |

Chemical

- | | | |
|----|---------------------|-------------------|
| 7. | Water Content | IEC : 61099 -2010 |
| 8. | Acidity | IEC : 61099 -2010 |
| 9. | Oxidation Stability | IEC : 61099 -2010 |

Electrical

- | | | |
|-----|-------------------------------|-------------------|
| 10. | Breakdown Voltage | IEC : 61099 -2010 |
| 11. | Dielectric dissipation factor | IEC : 61099 -2010 |
| 12. | DC Resistivity | IEC : 61099 -2010 |

CHECKED BY



TC 3545210



TC-5389

ELECTRICAL RESEARCH AND DEVELOPMENT ASSOCIATION

(Accredited by the National Accreditation Board for Testing and Calibration Laboratories, Govt. of India)

ERDA Road, Makarpura Industrial Estate, Vadodara-390 010, India.

EPABX : +91 (0265) 2642942, 2642964, 2642377, 3043128 / 29 / 30 / 31 / 33

Fax : +91 (0265) 2638382

E-mail : erda@erda.org

Web : http://www.erda.org



ULR No.: TC538924000006930F

Discipline: Electrical Testing

Group: Insulating Materials & Insulators

TEST REPORT No.: RP-2324-036777		DATE OF ISSUE : 23/03/2024		SHEET 3 of 4
Sr. No	Particular of tests & Cl. No.	Requirement as per specification	Obtained value	Remarks
1.	Appearance, (Cl. No.7.1.2)	Clear, free from water and suspended matter and sediment	Clear, free from water and suspended matter and sediment	Conforms
2.	Density at 20 °C kg/dm ³ (Cl. No.7.1.3)	Max. 1.000	0.963	Conforms
3.	Kinematic viscosity at 40°C , mm ² /s (Cl. No.7.1.4)	Max. 35	34	Conforms
4.	Flash Point, °C . Cl. No.7.1.5 The Ignitor type : Electric Absolute Barometric Pressure: 100.9 kPa	Min. 250	258	Conforms
5.	Fire Point , °C (Cl. No.7.1.5)	Min. 300	306	Conforms
6.	Pour point, °C (Cl. No.7.1.6)	Max. - 45	- 48	Conforms
7.	Water Content, mg/kg (Cl. No.7.1.8)	Max. 200	139	Conforms
8.	Oxidation Stability at 120°C, (164 Hrs.), Cl.No.7.1.10			
	a) Total Acidity, mg KOH/g	Max. 0.3	0.11	Conforms
	b) Total Sludge, % mass	Max. 0.01	0.002	Conforms
9.	Acidity, mg KOH/g, (Cl. No.7.1.9)	Max. 0.03	0.01	Conforms
10.	Breakdown voltage, kV , (Cl. No.8.1) -As received sample	Min. 45	78	Conforms
	a) Individual breakdown Voltages, kV: 73.1,76.5,78.2,82.9,75.8,80.5			
	b) Type of electrodes: Spherical			
	c) Frequency of the test voltage: 50 Hz			
	d) Oil temperature: 23.8°C			
	e) Stirrer used : Yes			
11.	Dielectric Dissipation factor at 90°C (Cl. No.8.2)	Max. 0.03	0.0028	Conforms
12.	DC Resistivity at 90°C, GΩ.m , (Cl. No. 8.2)	Min. 2	44.82	Conforms
Test Conditions for Dielectric Dissipation factor & D.C. Resistivity : - Type of Cell used: IEC : 60247 - 2004 (Fig. 1) - Average Voltage gradient in the sample while under test: 250 V/mm - Frequency of applied voltage: 50 Hz - Temperature of the room during test: 24.1°C - Humidity of the room during test: 37 % - Time of electrification : 1 Minute				
CHECKED BY 				



TC 3545211



TC-5389

ELECTRICAL RESEARCH AND DEVELOPMENT ASSOCIATION

(Accredited by the National Accreditation Board for Testing and Calibration Laboratories, Govt. of India)

ERDA Road, Makarpura Industrial Estate, Vadodara-390 010, India.

EPABX : +91 (0265) 2642942, 2642964, 2642377, 3043128 / 29 / 30 / 31 / 33

Fax : +91 (0265) 2638382

E-mail : erda@erda.org

Web : http://www.erda.org



ULR No.: TC538924000006930F

Discipline: Electrical Testing

Group: Insulating Materials & Insulators

TEST REPORT No.: RP-2324-036777

DATE OF ISSUE : 23/03/2024

SHEET 4 of 4



Photo of sample bottles in as received condition.

General
CHECKED BY

***** End of Test Report *****



TC 3545212