TEST REPORT

Test Report Issue To:
Savita Oil Technologies Limited
66/67, NAriman Bhavan, Nariman Point, Mumbai-400021

Test Report No : I231211009-1
Date of Issue: 22/12/2023

Sample Booking/Receipt : 11/12/2023
Date of Start of Testing: 12/12/2023
Date of Completion of Test: 12/12/2023

Customer Relationship Number : **A1120398**

Sample Description :
Transolsynth-100(Synthetic Ester Fluid)

Kind Attention: Mr. Amey Kulkarni
E-Mail: apkulkarni@savita.com
Contact No: 9920690908

Customer Reference Number :

Sample Drawn By : Test Sponsor

IGNITO LABS PVT. LTD. Authorised Signatory Faridabad, Haryana

Kaushal Kumar Thakur
Reviewed & Authorized By

This is Digitally Signed Report and hence doesn't require Physical Signature

1. INTRODUCTION

Determination of compliance of **Synthetic Ester Fluid** by performing fire point tests as per test methods referred by **R14** Category of **EN 45545-2:** Requirements for fire behavior of materials and components.

2. DOCUMENTS REFERRED

EN 45545-2:2020; Requirements for fire behavior of materials and components.
EN 60695-1-40; To determination the fire hazard of electrotechnical products- insulating liquids.
ISO 2592:2017; Determination flash and fire point of petroleum and related product by cleveland open cup method

Name of Product	Synthetic Ester Fluid
Trade Name	Transol Synth-100
Manufacturer	Savita Oil Technologies Limited, mumbai
Type of Material	Liquid oil
Density g/cc.	0.965

Parameter	Test method	Test result
Fire point °C (class k)	(ISO 2592-2017) (EN 60695-1-40)	320 °C

3. CONFORMITY

Tested specimen meets the Requirements of **R14 HL3 of EN 45545-2:2020.**

Parameter	Test Method	Requirements of R14 HL3 of EN 45545-2:2020	Observed Results	Conformity (Confirms/Does not confirms)
Fire point °C Class k	**T08 (EN 60695-1-40) (ISO 2592-2017)**	Minimum 300	320	**Confirms**

Classification Achieved: **R14 HL3 of EN 45545-2**

4. LIMITATION

The results only relate to the behavior of the specimen of the element of construction under the particular conditions of test; they are not intended to be the sole criteria of accessing the potential fire performance of the element in use nor do they reflect the actual behavior in fires.

----------End of Test Report----------

Anshul Kumar
(Tested By)

IGNITO LABS PVT. LTD. Authorised Signatory Faridabad, Haryana

Kaushal Kumar Thakur
(Reviewed & Authorized By)

Terms & Condition:

- The results are related only to the items Tested
- Total Liability of our Laboratory is limited to the invoiced Amount. No Liability will be accepted after Sample is taken back
- The Sample Description is given "As desired by the customers". Sample not drawn by us & Analysis Conducted on Received sample unless specified otherwise.
- Retained sample will be destroyed after 30 days from the date of issue of the test report unless instructed otherwise.
- Any Complaints or Retest request should be communicated within 15 days from the issue of the Test report.
- Test Report shall not be reproduced except in full, without Written approval of the Laboratory
- The Test report is not to be reproduced wholly or in parts & cannot be used as an evidence in a court of law & shall not be used in advertising media without our permission in writing.

Anshul Kumar
(Tested By)

IGNITO LABS PVT. LTD. Authorised Signatory Faridabad, Haryana

Kaushal Kumar Thakur
(Reviewed & Authorized By)