



Petroleum products — Transparent and opaque liquids — Determination of kinematic viscosity and calculation of dynamic viscosity

TECHNICAL CORRIGENDUM 1

Produits pétroliers — Liquides opaques et transparents — Détermination de la viscosité cinématique et calcul de la viscosité dynamique

RECTIFICATIF TECHNIQUE 1

Technical Corrigendum 1 to International Standard ISO 3104:1994 was prepared by Technical Committee ISO/TC 28, *Petroleum products and lubricants*.

Pages 6 and 7

14.1 Determinability

Add the following after: Residual fuel oils at 50 °C⁶): 0,017 γ (1,7 %)

Lubricant additives at 100 °C⁷):
0,00106 γ ^{1,1}

Gas oils at 40 °C⁸):
0,0013 ($\gamma + 1$)

Kerosines at – 20 °C⁹):
0,0018 γ

ICS 75.080

Ref. No. ISO 3104:1994/Cor.1:1997(E)

Descriptors: petroleum products, liquids, tests, determination, viscosity, kinematic viscosity, dynamic viscosity, rules of calculation, test equipment.

© ISO 1997

Printed in Switzerland

14.2 Repeatability

Add the following after: Residual fuel oils at 50 °C⁶⁾: $0,015 x$ (1,5 %)

Lubricant additives at 100 °C⁷⁾:
 $0,00192 x^{1,1}$

Gas oils at 40 °C⁸⁾:
 $0,0043 (x + 1)$

Kerosines at – 20 °C⁹⁾:
 $0,007 x$

14.3 Reproducibility

Add the following after: Residual fuel oils at 50 °C⁶⁾: $0,074 x$ (7,4 %)

Lubricant additives at 100 °C⁷⁾:
 $0,00862 x^{1,1}$

Gas oils at 40 °C⁸⁾:
 $0,0082 (x + 1)$

Kerosines at – 20 °C⁹⁾:
 $0,019 x$

Add to footnotes:

7) These precision values were obtained by statistical examination of interlaboratory results from eight additives in the range 145 mm²/s to 500 mm²/s at 100 °C, and were first published in 1997.

8) These precision values were obtained by statistical examination of interlaboratory results from eight gas oils in the range 1 mm²/s to 13 mm²/s at 40 °C, and were first published in 1997.

9) These precision values were obtained by statistical examination of interlaboratory results from nine kerosines (jet fuels) in the range 4,3 mm²/s to 5,6 mm²/s at – 20 °C, and were first published in 1997.