

Technical Data Sheet

Date of issuing : 01.07.2025
Product Name : Transformer Oil - Transol GA
Grade : ASTM D - 3487-2016 Type I

Rev. No. 2

Sr. No.	Properties	Test Method ASTM - 3487	Limit	Typical Value
[A] Physical				
1	Aniline Point, °C, min	D 611	63	78
2	Color, max	D 1500	0.5	< 0.5
3	Flash Point, °C, min	D 92	145	148
4	Interfacial Tension at 25 °C, min. dynes/cm	D 971	40	46
5	Pour Point, °C, max	D 97	- 40	- 42
6	Relative Density(Specific gravity), 15 °C/15 °C max	D 1298	0.91	0.865
6	Density at 29.5 °C, gm/cc	D 1298	-	0.860
7	Viscosity cSt, max	D 445		
	at 100 °C		3	2.7
	at 40 °C		12	11.0
	at 0 °C		76	70.0
8	Visual examination	D 1524	Clear & Bright	Clear & Bright
[B] Electrical				
9	Dielectric Breakdown Voltage at 60Hz			
	Disc electrodes, min, kV	D 877	30	68
	VDE electrodes, min. kV 0.040-in (1.02-mm)	D 1816	20	42
	0.080-in. (2.03-mm) gap		35	60
10	Dielectric Breakdown voltage, Impulse conditions	D 3300	145	174
	25 °C, min, kV, needle negative to sphere grounded. 1 - in. (25.4 - mm) gap			
11	Gassing Tendency, max., µL/min	D 2300	+ 30	+ 3
12	Dissipation factor(or power factor), at 60 Hz max, %	D 924		
	25 °C		0.05	0.018
	100 °C		0.30	0.10
[C] Chemical				
13	Oxidation stability (acid-sludge test)	D 2440		
	72 h: % sludge, max. by mass		0.15	0.04
	Total acid number, max. mg KOH/ g		0.5	0.08
	164 h: % sludge, max. by mass		0.3	0.05
	Total acid number, max. mg KOH/ g		0.6	0.16
14	Oxidation stability (rotating bomb method), min, minutes	D 2112	-	-
15	Oxidation inhibitor content, max, % by mass	D 2668	0.08	0.075
16	Corrosive Sulphur	D 1275	Non - Corrosive	Non - Corrosive
17	Water, max, ppm	D 1533	35	14
18	Neutralisation number, total acid number, max, mgKOH/ g	D 974	0.03	0.0013
19	P.C.B. Content, ppm	D 4059	Not detectable	Not detectable


Authorised Signatory