

Technical Data Sheet

Date : 01.07.2025
Product Name : Transformer Oil TRANSOL - GB II
Grade : BS 148 : 1998 Class - II

Rev - 2

Sr. No.	Property	Test Method BS : 148 : 1988	Specified Values	Typical Test Values
1	Kinematic Viscosity mm ² / Sec At 40 °C At - 30 °C	BS EN ISO 3104	Max. 11 Max. 1800	10.5 1010
2	Flash Point, °C ,	BS EN 22719	Min. 130	148
3	Pour Point, °C ,	BS 2000 Part 15	Max. - 45	- 48
4	Appearance	Representative sample of the Oil shall be examined in a 100 mm thick layer at 27 °C	Clear, free from sediment & suspended matter	Clear, free from sediment & suspended matter
5	Density at 20 °C, kg / dm ³ Density at 29.5 °C, kg / dm ³	BS EN ISO 3675	Max. 0.895	0.861 0.856
6	Neutralisation Value, mg KOH /g	BS 2000 Part 1	Max. 0.03	0.0014
7	Corrosive Sulphur	BS 5680 1979	Non - Corrosive	Non - Corrosive
8	Water Content, mg / kg a) bulk delivery b) drum delivery	IEC 814	Max.20 Max.30	12 14
9	Anti - oxidant additives	BS 5984 1980	Not detectable	Not detectable
10	Oxidation stability, 164 hrs.	BS EN 61125 : 1993	Max.1.5 Max. 1.0	0.42 0.24
11	Breakdown Voltage : as delivered, kV After treatment, kV	BS EN 60156	Min. 30 Min. 50	70
12	Dielectric Dissipation Factor at 90 °C & 40 to 60 Hz	BS 5737	Max. 0.005	0.0005
13	Gassing tendency at 50 Hz after 120min. mm ³ / min Method A	BS 5797 Method A	Max. +5	+ 3.0
14	Total PCB Content, mg/kg	BS EN 61619	Not detectable	Not detectable
15	Total furans , mg/kg	BS EN 61198	Max. 1.0	NIL
16	Polycyclic aromatics , % mass	BS 2000 : Part 346	Max. 3.0	0.50


Authorised Signatory