

Technical Data Sheet

Date of issuing : 12.02.2026
Product Name : Transformer Oil - Transol GAPX
Grade : ASTM D - 3487-2025 Type II

Rev. No. 3

Sr.No.	Properties	Test Method ASTM - 3487	Limit	Typical Values
A)	Physical			
1	Aniline Point, min, °C	D 611	63	110
2	Color, max	D 1500	0.5	< 0.5
3	Flash Point, min, °C	D 92	145	148
4	Interfacial Tension at 25 °C, min. mN/m	D 971	40	46
5	Pour Point, max, °C	D 97	- 40	- 42
6	Relative Density(Specific gravity), 15 °C/15 °C max	D 1298	0.91	0.829
	Density at 29.5 °C, gm/cc	D 1298	-	0.820
7	Viscosity, max, mm ² /s at	D 445		
	100 °C		3	2.36
	40 °C		12	8.20
	0 °C		76	41.0
8	Visual examination	D 1524	Clear & Bright	Clear & Bright
B)	Electrical			
9	Dielectric breakdown voltage at 60Hz VDE electrodes, min. kV 1 mm gap	D 1816	20	40
	2 mm gap		35	60
10	Dielectric breakdown voltage, Impulse condition negative polarity point, min, kV	D 3300	145	180
11	Gassing Tendency, max., µL/minute	D 2300	+ 30	+ 8
12	Dissipation factor(or power factor), at 60 Hz max, %	D 924		
	25 °C		0.05	0.015
	100 °C		0.30	0.050
C)	Chemical			
13	Oxidation stability (acid-sludge test) 72 h:	D 2440		
	sludge, max, % by mass		0.1	0.04
	Total acid number, max. mg KOH/ g		0.3	0.06
	164 h:			
	sludge, max, % by mass		0.2	0.06
	Total acid number, max. mg KOH/ g		0.4	0.14
14	Oxidation stability (pressure vessel test), min, minutes	D 2112	195	280
15	Oxidation inhibitor content, max, % by mass	D 2668	0.3	0.28
16	Corrosive sulfur	D 1275	Non - Corrosive	Non - Corrosive
17	Water, max, mg/kg	D 1533	35	15
18	Neutralisation number, total acid number, max, mgKOH/ g	D 974	0.03	0.0014
19	Furanic compounds, max per compound, µg/L	D5837	25	Not detectable
20	PCB Content, mg/kg	D 4059	Not detectable	Not detectable


Authorised Signatory