

SPECIFICATION

Iron Oxide Yellow 3910

| ITEM | STANDARD Specification |
|--|---------------------------|
| Fe ₂ O ₃ content | 86.0 % Min |
| Matter volatile at 105 C | 1.0% Max. |
| Water Soluble Matter | 0.30 % Max |
| Residue on 320 Mesh | 0.30 % Max |
| Oil Absorption | 25 – 35 g/100g |
| PH Value | 3.5 – 7.0 |
| Tinting Strength Compare with Standard | 92 – 102 % |
| | |
| | |
| | |