
(a)
Fe–36Cr
spinodal window
(Fig. 1b)
Δf_{SAW}, random → ϕ = 1 (%)
x_{Cr}
(b)
unallowed range begins (609 MHz)
Highest (P)SAW, 10^4 grains (MHz)
MD, random alloy
MD, fully decomposed (ϕ = 1)
x_{Cr}