
(a)
Razumovskiy et al. [8]
DFT (this work)
MD, random alloy
C_{11} (GPa)
x_{Cr}
(b)
marker = fastest grain
Razumovskiy et al. [8]
DFT (this work)
MD, random alloy
unallowed for pristine CASS [1]
(P)SAW frequency (GHz), λ = 6.4 µm
C_{11} (GPa)