

(a)
Razumovskiy et al. [8]
DFT (this work)
MD, random alloy
MD, fully decomposed (ϕ = 1)
C11 (GPa)
xCr
(b)
Razumovskiy et al. [8]
DFT (this work)
MD, random alloy
MD, fully decomposed (ϕ = 1)
Frequency (GHz), λ = 6.4 μm
bulk (quasi-longitudinal) waves
unallowed for pristine CASS [1]
(P)SAW
C11 (GPa)
(c)
MD cells behind the green tensors in (b), 25³ cells, outer faces: random alloy and fully decomposed structure at three compositions
Fe
Cr
20% Cr, random
20% Cr, ϕ = 1
36% Cr, random
36% Cr, ϕ = 1
50% Cr, random
50% Cr, ϕ = 1
MD C11 (GPa)
245
+1.5%
249
247
+4.1%
257
254
+5.0%
266
MD fSAW (GHz, 6.4 μm)
0.457
+2.6%
0.469
0.451
+5.1%
0.474
0.455
+5.5%
0.480