

(a)
Razumovskiy et al. [8]
DFT (this work)
MD, random alloy
MD, fully decomposed (ϕ = 1)
C11 (GPa)
xCr
(b)
Razumovskiy et al. [8]
DFT (this work)
MD, random alloy
MD, fully decomposed (ϕ = 1)
Frequency (GHz), λ = 6.4 μm
bulk (quasi-longitudinal) waves
unallowed for pristine CASS [1]
(P)SAW
C11 (GPa)
(c)
MD cells behind the green tensors in (b), one (001) plane: random alloy and fully decomposed structure at three compositions
Fe
Cr
20% Cr, random
20% Cr, ϕ = 1
36% Cr, random
36% Cr, ϕ = 1
50% Cr, random
50% Cr, ϕ = 1
MD C11 (GPa)
+1.5%
245
249
+4.1%
247
257
+5.0%
254
266
MD fSAW (GHz, 6.4 μm)
+2.7%
0.456
0.469
+5.0%
0.451
0.473
+5.7%
0.454
0.480