

(a)
Demixing free energy (eV/atom)
x_{Cr}
Muffin-tin approximation
GGA (this work)
Experimental
PWSCF-PAW
SIESTA-NC
GGA (QE, this work), relaxed a
GGA (QE, this work), experimental a
(b)
unstable: curvature > 0 (shaded)
$\partial^2 \Delta G / \partial x_{Cr}^2$ (eV/atom)
x_{Cr}
quadratic fit to two-point values
two-point differences
exact (PWSCF-PAW model)
three-point differences
(c)
Fully decomposed MD structures (ϕ = 1), one (001) plane of a 25^3 bcc cell: two phases form inside the spinodal window
Fe
Cr
10% Cr
20% Cr
36% Cr
50% Cr
70% Cr
95% Cr
ΔG_{demix} (meV/atom)
+3
−22
−62
−72
−50
−9
0
(d)
DFT cells, relaxed in QE: bcc unit cells and 40-atom SQS (2×2×5); Cr moments vanish at 35−50% Cr
Fe
Cr
↑ moment
bcc Fe
20% Cr, SQS
35% Cr, SQS
50% Cr, SQS
65% Cr, SQS
95% Cr, SQS
bcc Cr
QE $\langle m_{Fe} \rangle$ (μ_B)
2.19
2.22
2.14
2.05
1.92
1.41
QE $\langle m_{Cr} \rangle$ (μ_B)
−0.58
−0.21
−0.03
+0.01
+0.03
0