

(a)
Razumovskiy et al. [8]
DFT (this work)
MD, random alloy
C_{11} (GPa)
x_{Cr}
(b)
Razumovskiy et al. [8]
DFT (this work)
MD, random alloy
MD, fully decomposed (ϕ = 1)
Frequency (GHz), λ = 6.4 μm
bulk (quasi-longitudinal) waves
unallowed for pristine CASS [1]
(P)SAW
C_{11} (GPa)