
(a)
Razumovskiy et al. [8]
DFT (this work)
MD, random alloy
MD, fully decomposed (ϕ = 1)
C11 (GPa)
xCr
(b)
unallowed range maximum
unallowed range minimum
Razumovskiy et al. [8]
DFT (this work)
unallowed for a homogeneous solid solution
fSAW (GHz), λ = 5.5 μm
C11 (GPa)