Chemical Compatibilities Strongcoat EN100

TEST Chemical resistance test on Strongcoat EN100

PROCEDURE Immersion for 1, 3 and 14 days

CHEMICAL RESISTANCE TABLE

	CONCENTRATION	RESISTANCE		
		DAY 1	DAY 3	DAY 14
Acetic Acid	Up to 30%	R	R	RS
Acetic Acid	Up to 50%	NR	NR	NR
Acetic Acid	Up to 98%	NR	NR	NR
Hydrochloric Acid	Up to 20%	RS	RD	RD
Hydrochloric Acid	Up to 32%	RS	RD	RD
Sulfuric Acid	Up to 30%	RS	RD	RD
Sulfuric Acid	Up to 50%	RD	RD	NR
Sulfuric Acid	Up to 98%	NR	NR	NR
Phosphoric Acid	Up to 30%	RD	RD	RD
Phosphoric Acid	Up to 50%	RD	RD	RD
Phosphoric Acid	Up to 85%	RD	RD	RD
Lactic Acid	Up to 20%	RS	RD	RD
Lactic Acid	Up to 30%	RD	RD	RD
Lactic Acid	Up to 50%	RD	RD	RD
Lactic Acid	Up to 90%	RD	NR	NR
Citric Acid	Up to 20%	R	R	R
Citric Acid	Up to 50%	R	R	R
Soda Lye	Up to 50%	R	R	R
Caustic Potash	Up to 50%	R	R	R
Oleic Acid		R	R	R
Triethanolamine		R	R	R
Antifungus		R	R	R
Benzyl Alcohol		R	RS	RS
Brake Fluid		R	R	R
Methanol		R	R	R
Ethanol		R	R	R
Isopropanol		R	R	R
Glycerin		R	R	R
Solvent Naphtha		R	R	R

Chemical Compatibilities
Strongcoat EN100

	CONCENTRATION	RESISTANCE		
		DAY 1	DAY 3	DAY 14
Ethyl Benzene		R	R	R
Ethylene Glycol		R	R	R
Sodium Chloride	Up to 20%	R	R	R
Sugar	Up to 10%	R	R	R
Hydraulic Oil		R	R	R
Silicone Oil		R	R	R
Acetone		NR	NR	NR
Toluene		R	R	R
Xylene		R	R	R
Benzene		R	R	RS
Diesel		R	R	R
Water		R	R	R
Distilled Water		R	R	R
Hybex	Up to 10%	R	R	R
Hand Wash Soap		R	R	R
Flash		RS	RD	RD
PRX Iso-octane, Toluene 50:50		R	R	R
PRX Methanol, Isopropanol, Water 48:48:4		R	R	R

R: Resistant
RS: Resistant with slight discolouration
RD: Resistant with obvious colour change
NR: Non-resistant

Chemical Compatibilities
Strongcoat EN100

PROCEDURE Spot test at 1 hour

CHEMICAL RESISTANCE TABLE

	CONCENTRATION	RESISTANCE
Acetic Acid	Up to 10%	R
Ammonium Chloride		R
Ammonium Ferrous Sulphate		R
Ammonium Hydroxide	Up to 30%	R
Ammonium Thiocyanate		R
Benzene		R
Benzoyl Chloride		R
Benzyl Alcohol		R
Bleach (Sodium Hypochlorite)		R
Boric Acid	Up to 1%	R
Brake Fluid		R
Car Oil		R
Carbon Tetrachloride		R
Castor Oil		R
Citric Acid	Up to 50%	R
Deionised Water		R
Diesel		R
Ethylene Glycol		R
Fatty Acids		R
Ferrous Sulphate		R
Formaldehyde	Up to 37%	R
Fumaric Acid	Up to 0.5%	R
Gasoline		R
Hexamine	Up to 25%	R
Hexane		R
Hydrochloric Acid	Up to 35%	RS
Isopropanol		R

	CONCENTRATION	RESISTANCE
Kerosene		R
Lactic Acid	Up to 20%	R
Magnesium Sulphate		R
Methyl Isobutyl Ketone		R
Mineral Spirit		R
Nicotinic Acid	Up to 2%	R
Nitric Acid	Up to 10%	R
Phosphoric Acid	Up to 10%	R
Potassium Chromate		R
Potassium Hydroxide	Up to 50%	R
Potassium Sodium Tartrate		R
Potassium Sulphate		R
Propylene Glycol		R
Sea Water		R
Sodium Benzoate		R
Sodium Hydroxide	Up to 50%	R
Sodium Thiocyanate-anhydrous		R
Sulphuric Acid	Up to 98%	RS
Tartaric Acid	Up to 50%	R
Toluene		R
Vegetable Oils		R
Xylene		R
Zinc Acetate		R

R: Resistant
RS: Resistant with slight discolouration