DonProof AL

Single component, aliphatic polyurethane UV protective topcoat for polyurea membranes

DESCRIPTION

DonProof AL is a single component, polyurethane based, aliphatic topcoat with high solid content and high UV resistance. It is designed as an elastic protective topcoat for polyurea waterproofing membranes DonProof PU range.

DonProof AL cures with the humidity in the air to form a seamless, flexible and coloured film layer over the membrane. Due to its aliphatic structure, DonProof AL preserves its colour when exposed to sunlight and does not fade or turn yellow, protecting the underlying aromatic polyurea membrane from UV exposure.

APPLICATIONS

DonProof AL is designed as a UV protective and finishing topcoat over polyurea membranes on areas such as:

- Exposed roofs, flat and sloped.
- Balconies, terraces and podium decks.
- Areas exposed to pedestrian traffic.
- Surfaces requiring high abrasion resistance.

ADVANTAGES

- Single component, supplied ready for use.
- Aliphatic structure; preserves its colour and does not yellow when exposed to sunlight.
- High solid content.
- High elasticity; accommodates the movement of the underlying polyurea membrane.
- Excellent abrasion resistance.
- Applied directly over polyurea without the need for a primer.
- Forms a seamless, jointless finish.
- Easy application by brush, roller or airless spray.

METHOD OF USE

SUBSTRATE PREPARATION

The polyurea membrane must be sound, clean, dry, undamaged and free from dust, oil, grease and other contaminants. A clean surface will ensure maximum adhesion between the membrane and DonProof AL.

Where DonProof AL is applied over an existing or aged polyurea membrane, the membrane should be inspected to ascertain if any damage is present. Damaged areas should be repaired, and the surface cleaned before applying DonProof AL. Consult DCP Technical Department for the recommended surface cleaning procedure.

TECHNICAL PROPERTIES:

Colour:	White *(other colours available upon request)*
Density:	1.43 ± 0.02 g/cm³
Viscosity:	8 - 16 P
Solid content by weight:	85 - 88% @ 105°C
Tack free time:	4 - 6 hr @ RH 55 ± 5%
Shore A hardness: ASTM D2240	50 ± 5 @ 7 days
Tensile strength: ASTM D412	> 4 MPa @ 7 days
Elongation at break: ASTM D412	> 400% @ 7 days
Tear strength: ASTM D624, Die C	> 18 N/mm
Bond adhesion over polyurea:	> 1.5 MPa (1 coat @ 200 microns)

PRIMING

No primer is needed when DonProof AL is applied as a topcoat over polyurea membranes. For application over any other substrate, consult DCP Technical Department.

MIXING

DonProof AL is a single component product. Before application, stir the content of the pack using a low speed mixer until uniform colour and consistency are achieved. Care should be taken not to entrap air into the material while mixing; entrapped air will show as visible bubbles on the cured surface.

DonProof AL

APPLICATION

DonProof AL can be applied by brush, roller or airless spray machine. The first coat should be applied to obtain a continuous uniform coating.

The second coat (if needed) should be applied within the minimum overcoating time (7 - 8 hours) to achieve the maximum adhesion between the two coats.

CLEANING

All tools should be cleaned immediately after application using DCP Solvent. Hardened materials must be cleaned mechanically.

PACKAGING

DonProof AL is available in 5kg and 20kg packs.

COVERAGE

Approximately 2.5 - 3.5 m²/kg per coat.

Coverage figures are theoretical; actual consumption depends on the application method, site conditions and the profile of the polyurea membrane.

STORAGE

Donproof AL, have a shelf life of 12 months from date of manufacture if stored in dry conditions at a temperature between 5°C and 25°C in original unopened packs.

If these conditions are exceeded, contact DCP Technical Department for advice.

CAUTIONS

HEALTH AND SAFETY

DonProof AL should not come in contact with skin or eyes. Goggles and gloves should be used.
In case of accidental contact with eyes, immediately flush with plenty of water for at least 10 minutes and seek medical advice if necessary.

For further information refer to the Material Safety Data Sheet.

FIRE

Donproof AL is flammable.

MORE FROM DON CONSTRUCTION PRODUCTS

A wide range of construction chemicals products are manufactured by DCP which include:

- Concrete admixtures.
- Surface treatments
- Grouts and anchors.
- Concrete repair.
- Flooring systems.
- Protective coatings.
- Sealants.
- Waterproofing.
- Adhesives.
- Tile adhesives and grouts.
- Building products.
- Structural strengthening.

Note:
We endeavour to ensure that any information, advice or recommendation we may give in product literature is accurate and correct. However, because we have no control over where and how products are applied, we cannot accept any liability arising from the use of the products.