DonProof Primer EP

Epoxy-based primer for polyurea systems

DESCRIPTION

DonProof Primer EP is a two-component, epoxy-based primer enhanced with fillers. It is designed for surface preparation prior to the application of polyurea systems.

METHOD OF USE

SUBSTRATE PREPARATION

The substrate must be clean, dry, even, dense and free from oil, grease, dust and other contaminants. A clean surface will ensure maximum adhesion between the substrate and the coating.

Concrete floors must have a minimum compressive strength of 25 MPa and a maximum concrete relative humidity of 75% (max. moisture content of 5%), relative humidity can be measured using a hygrometer. Concrete relative humidity should be less than 75% for concrete 28 days old or more.

Unsound layers and contaminated concrete surfaces must be prepared using mechanical surface removing equipment. Acid etching can be used only in well-ventilated areas. Areas deeply contaminated by oil or grease should be treated by hot compressed air.

MIXING

Prior to mixing, stir the individual components to disperse any settlement. Transfer the entire contents of the hardener into the resin component and using a Jiffy-type mixer attached to a slow running electric drill, or the rotary drum mixer, mix for approximately two minutes until a lump-free consistency is obtained. It is important to use a slow-speed mixer operating at 300 - 400 rpm to avoid entrapping air and to achieve a homogeneous mixture.

APPLICATION

DonProof Primer EP should be applied using a brush or a short pile lambswool roller. Ensure the primer is spread evenly at the specified coverage rate, avoiding any ponding on the surface. On highly porous substrates, a second coat may be necessary.

TECHNICAL PROPERTIES @ 25°C:	
Colour:	Light beige
Mixed density:	1.35 ± 0.05 g/cm³
Pot life:	30 - 60 min
Overcoating time:	12 - 24 hr
Bond strength: ASTM D4541-85	≥ 3 MPa (concrete failure)
VOC: ASTM D2369	< 20 g/ltr

CLEANING

Tools can be cleaned using DCP Solvent prior to setting.

PACKAGING

DonProof Primer EP is available in 5 kg and 20 kg packs.

COVERAGE

DonProof Primer EP is applied at a coverage rate of 3.5 - 3.7 m²/kg to achieve a dry film thickness of approximately 200 micron per coat.

STORAGE

DonProof Primer EP has a shelf life of 12 months from date of manufacture if stored at temperatures between 5°C and 40°C.

If these conditions are exceeded, contact DCP Technical Department for advice.

DonProof Primer EP

CAUTIONS

HEALTH AND SAFETY

DonProof Primer EP should not come in contact with skin and eyes.
In case of accidental splashes to the eyes, wash immediately with clean water and seek medical advice.

For further information refer to the Material Safety Data Sheet.

FIRE

DonProof Primer EP is nonflammable.

MORE FROM DON CONSTRUCTION PRODUCTS

A wide range of construction chemical products are manufactured by DCP which include:

- Concrete admixtures.
- Surface treatments
- Grouts and anchors.
- Concrete repair.
- Flooring systems.
- Protective coatings.
- Sealants.
- Waterproofing.
- Adhesives.
- Tile adhesives and grouts.
- Building products.
- Structural strengthening.

Note:
We endeavour to ensure that any information, advice or recommendation we may give in product literature is accurate and correct. However, because we have no control over where and how products are applied, we cannot accept any liability arising from the use of the products.