DonProof DPM

Epoxy damp-proof membrane and primer for polyurea systems

DESCRIPTION

Donproof DPM is a two pack, solvent free epoxy based damp-proof membrane and primer, designed specifically for the application of polyurea membranes onto substrates with a high moisture content.

It suppresses residual construction moisture and rising dampness in concrete and sand/cement screeds and can be used in situations where the relative humidity level is above 75% under which spray-applied polyurea would otherwise be at risk of osmotic blistering, pin-holing and adhesion loss. It is applied by brush or roller in one or two coats depending on the relative humidity of the floor.

METHOD OF USE

SUBSTRATE PREPARATION

The substrate must be clean, dry, even, dense and free from oil, grease, dust and other contaminants. A clean surface will ensure maximum adhesion between the substrate and the coating. Concrete floors must have a minimum compressive strength of 25 MPa.

Unsound layers and contaminated concrete surfaces must be prepared using mechanical surface removing equipment.

Acid etching can be used only in well ventilated areas. Areas deeply contaminated by oil or grease, should be treated by hot compressed air.

MIXING

Prior to mixing, stir individual components of DonProof DPM. Take care to ensure that bottom and sides are thoroughly scraped, transfer the entire content of hardener into the base and mix for 2 - 3 minutes using slow speed mixer fitted with suitable paddle.

APPLICATION

DonProof DPM should be applied by brush or short hair lambs wool roller.

One coat of DonProof DPM is required where the relative humidity level of the screed is between 75% and 85%. For RH levels between 86% and 98%, use 2 coats.

Spread evenly at the recommended coverage rate, avoiding any primer ponding on the floor. Highly porous surfaces may require two coats of primer.

TECHNICAL PROPERTIES @ 25°C:

Appearance:	Light beige Other colours are available upon request
Mixed density:	1.35 ± 0.05 g/cm³
Pot life:	30 - 60 min
Overcoating time:	12 - 24 hr
Bond strength: ASTM D4541-85	≥ 3 MPa (concrete failure)
VOC:	< 20 g/ltr

CLEANING

Tools can be cleaned using DCP Solvent prior to setting.

PACKAGING

DonProof DPM is available in 5 kg packs.

COVERAGE

DonProof DPM is applied at a coverage rate of 3.5 - 3.7 m²/kg to achieve approximately 200 micron DFT per coat.

STORAGE

DonProof DPM has a shelf life of 12 months from date of manufacture if stored at temperatures between 5°C and 40°C.

If these conditions are exceeded, contact DCP Technical Department for advice.

DonProof DPM

CAUTIONS

HEALTH AND SAFETY

DonProof DPM should not come in contact with skin and eyes.
In case of accidental splashes to the eyes, wash immediately with clean water and seek medical advice.

For further information refer to the Material Safety Data Sheet.

FIRE

DonProof DPM is nonflammable.

Flash Point:
DCP Solvent: 33°C.

MORE FROM DON CONSTRUCTION PRODUCTS

A wide range of construction chemical products are manufactured by DCP which include:

- Concrete admixtures.
- Surface treatments
- Grouts and anchors.
- Concrete repair.
- Flooring systems.
- Protective coatings.
- Sealants.
- Waterproofing.
- Adhesives.
- Tile adhesives and grouts.
- Building products.
- Structural strengthening.

Note:
We endeavour to ensure that any information, advice or recommendation we may give in product literature is accurate and correct. However, because we have no control over where and how products are applied, we cannot accept any liability arising from the use of the products.