


# PASS

**SUBMITTER**

Master Creation  
 Shop No.70-A Ground Floor, Ward No.418/A, Millenium Textile Market-2, Ring Road, Surat, Gujarat, 395002, India



Report Number  
(8720)305-0218

**STYLE  
NUMBER**

HAPPY ROADTRIP

**PRODUCT  
DESCRIPTION**

100% POLYESTER POLY AMERICAN CREPE, SNOW WHITE

**EXECUTIVE  
SUMMARY**

The submitted sample(s) MEET all the tested requirement(s).

**REMARKS**

/

**TECHNICAL  
QUESTIONS**

Vijith K P  
 Directline +91-080-40701600.Ext:684  
[vijith.kp@in.bureauveritas.com](mailto:vijith.kp@in.bureauveritas.com)

**SIGNATURES**

Bureau Veritas Consumer Products Services (I) Pvt Ltd



**GENERAL  
INFORMATION**

Pradipta Kr. Lenka  
 Directline +91-080-40701600.Ext:632  
[pradipta.kumar@in.bureauveritas.com](mailto:pradipta.kumar@in.bureauveritas.com)

Vijith K P  
 Program Manager  
 Softlines Department

**Note:** The submitted samples were not drawn by the laboratory



BUREAU  
VERITAS

Test Report: (8720)305-0218  
MYNTRA JABONG INDIA (P) LTD

Received Date: October 31, 2020

Report Date: November 03, 2020

BRAND	dressberry
TEST ITEM	Fabric
SAMPLE QUANTITY	2MTR
COLOUR	SNOW WHITE
STYLE REFERENCE NO.	DB_SS21_W_DR_SHTJ32_03-B
COUNTRY OF ORIGIN	INDIA
FABRIC MILL NAME	K.N.DESIGNER
MANUFACTURER	K.N.DESIGNER
ORDER/PO NO.	N/A
PI / PO NO.	/
FABRIC CONSTRUCTION	100% POLYESTER
SEASON	SS21
FABRIC WEIGHT	95 GSM
WOVEN OR KNITS OR DENIM	Woven
DIVISION/DEPARTMENT	Women's
TOPS OR BOTTOM	Dresses
COUNTRY OF DESTINATION	INDIA
END USE	WOMEN'S WEAR
YARN COUNT	N/A
SIZE	N/A
AGE RANGE	N/A
TYPE OF FINISH/DYE	PRINT
TYPE OF PRINT	DIGITAL PRINT
SOLE MATERIAL	/
ORDER QUANTITY	1095 MTR
ADDITIONAL INFORMATION	/
SUBMITTED FIBER CONTENT	100% POLYESTER
ACTUAL FIBER CONTENT	/
SUGGESTED FIBER CONTENT	/



**BUREAU  
VERITAS**

**Test Report: (8720)305-0218**  
**MYNTRA JABONG INDIA (P) LTD**

Received Date: October 31, 2020

Report Date: November 03, 2020

<b>SUBMITTED CARE INSTRUCTION(S)</b>	machine wash cold tumble dry low
<b>CLIENT EXPECTED CARE INSTRUCTION</b>	/
<b>SUGGESTED CARE INSTRUCTION(S)</b>	/
<b>RANGE</b>	/
<b>GENDER</b>	/
<b>VENDOR ARTICLE NO.</b>	/
<b>PROTOCOL NUMBER</b>	MYNT-SL-PTCL-00301-IND-WOVEN FABRIC DENIM FABRIC-V9
<b>PROTOCOL STAR LEVEL</b>	/
<b>FAIL RETEST</b>	NO
<b>PREVIOUS REPORT NUMBER</b>	/
<b>RETEST SAMPLE NUMBER</b>	/
<b>FABRIC REPORT NUMBER</b>	/
<b>REPORT EXPIRATION DATE</b>	/



**BUREAU  
VERITAS**

# Test Report: (8720)305-0218 MYNTRA JABONG INDIA (P) LTD

Received Date: October 31, 2020

Report Date: November 03, 2020

## TEST RESULTS FOR 100% POLYESTER POLY AMERICAN CREPE

TESTED PROPERTY	REQUIREMENTS	RESULTS	RATING
Linear Density of Yarn Removed from Woven Fabric (ISO 7211-5:1984)			
Snow White			DATA
warp (D)	MYNT-SL-301-IND-V9	76.9 D	
weft (D)	-5 to 5 %	101.7 D	
Fabric count of woven fabric (ASTM D3775-17e1)			
Snow White			DATA
Ends	MYNT-SL-301-IND-V9	128 per inch	
Picks	Provide test results. No PASS/FAIL comment. ( As Claim (N/A))	90 per inch	
Dimensional Changes of Fabrics in Washing (ISO 3759:2011 / ISO 5077:2007 / ISO 6330:2012 (Mod))###			
3N, LINE DRY, 3 MACHINE WASHES			PASS
Snow White			
		Dimensional Change(%)	
Lengthwise	Dimensional Change -3 to 3 %	-0.1	
Widthwise	Dimensional Change -3 to 3 %	-0.1	
Tear properties of fabrics: Ballistic Pendulum Method (Elmendorf) (ISO 13937-1:2000)			
Snow White			PASS
Across Warp	MYNT-SL-301-IND-V9 Min. 800 gf	1305.6 gf	
Across Weft	Min. 700 gf	1228.8 gf	
Colourfastness to rubbing (ISO 105-X12:2016)			
Snow White			PASS
Colour Staining - Dry	MYNT-SL-301-IND-V9 Min. Grade 4	Grade 4-5	
Colour Staining - Wet	Min. Grade 3-4	Grade 4-5	
Colourfastness to washing (AATCC 61-13 / SASO ISO 105-C10:2006)###			
Snow White			PASS
Colour Change	MYNT-SL-301-IND-V9 Min. Grade 4	Grade 4	
Self Staining	/	Grade 4-5	
Colour Staining on Acetate	Min. Grade 3-4	Grade 4-5	
Colour Staining on Cotton		Grade 4-5	
Colour Staining on Polyamide		Grade 4-5	
Colour Staining on Polyester		Grade 4-5	
Colour Staining on Acrylic		Grade 4-5	
Colour Staining on Wool		Grade 4-5	
Colorfastness Rating			

**TEST RESULTS FOR 100% POLYESTER POLY AMERICAN CREPE**

TESTED PROPERTY	REQUIREMENTS	RESULTS	RATING
Color Change		Color Stain / Self Staining	
5 - Negligible or No Change		5 - Negligible or No Staining	
4 - Slightly Changed		4 - Slightly Stained	
3 - Noticeably Changed		3 - Noticeably Stained	
2 - Considerably Changed		2 - Considerably Stained	
1 - Much Changed		1 - Heavily Stained	

### Non-accredited test under NABL scope

END OF REPORT