



BUREAU  
VERITAS

# MYNTRA JABONG INDIA (P) LTD TEST REPORT

Technical Report: (8719)017-0130

Page 1 of 4  
January 19, 2019



Report Number  
(8719)017-0130

Certificate No. TC-6092 (Pls Refer the website [www.nabl-inida.org](http://www.nabl-inida.org) to view the scope of accreditation)

Bureau Veritas Consumer Products Services (I) Pvt. Ltd.  
AKR Tech Park, Ground floor,  
C Block, Survey no 112,  
BANGALORE  
Tel: 0091-80-40701600 Fax: 0091-80-40701655

This report is governed by, and incorporates by reference, CPS Conditions of Service as posted at the date of issuance of this report at <http://www.bureauveritas.com/home/about-us/our-business/cps/about-us/terms-conditions/> and is intended for your exclusive use. Any copying or replication of this report to or for any other person or entity, or use of our name or trademark, is permitted only with our prior written permission. This report sets forth our findings solely with respect to the test samples identified herein. The results set forth in this report are not indicative or representative of the quality or characteristics of the lot from which a test sample was taken or any similar or identical product unless specifically and expressly noted. Our report includes all of the tests requested by you and the results thereof based upon the information that you provided to us. Measurement uncertainty is only provided upon request for accredited tests. You have 60 days from date of issuance of this report to notify us of any material error or omission caused by our negligence or if you require measurement uncertainty; provided, however, that such notice shall be in writing and shall specifically address the issue you wish to raise. A failure to raise such issue within the prescribed time shall constitute your unqualified acceptance of the completeness of this report, the tests conducted and the correctness of the report contents.



# MYNTRA JABONG INDIA (P) LTD TEST REPORT

TO: AJANTA SILK

LAB NO.: (8719)017-0130  
FORM NO.: 233318 AU^  
DATE IN: Jan 17, 2019  
DATE OUT: Jan 19, 2019  
BRAND: DRESSBERRY  
NO. OF WORKING DAYS: 03  
PAGE 2 OF 4

ATTN: WASIM PINJARA

## OVERALL RATING

PASS X  
FAIL \_\_\_\_\_  
DATA \_\_\_\_\_

Vendor:	AJANTA SILK	Agent:	/
Fabric Supplier/Mill:	AJANTA EXPORTS	Factory/Manufacturer:	AJANTA SILK
P.O. No.:	/	Style No.:	CLOVER POLKA-A
Sample Description:	WOVEN 100% POLYESTER MOSS CREPE FABRIC, SAMPLE RECEIVED IN GOODCONDITION (DEPT:WOMENS) (ORDER QUANTITY:2126 MTR)	Style Reference No:	/
Color:	HARVEST GOLD	Country of Origin:	INDIA
Claimed Fabric Weight:	115 GSM	Fabric Construction:	/
Yarn Size:	/	Submitted Size:	/
Season:	SS19	FPU No.:	/
Type Of Print:	OVER PRINT	End Use:	WOMENS WEAR

Product Category	WOVEN FABRIC
Test Requested	FULL PACKAGE TEST
Previous Report No.	/

Submitted Fiber Content	100% POLYESTER
Actual Fiber Content	/
Suggested Fiber Content	/
Submitted Care Instruction(s)	MACHINE WASH COLD,TUMBLE DRY LOW



**BUREAU  
VERITAS**

LAB NO: **(8719)017-0130**

Page 3 of 4

TEST PROPERTY	PASS	FAIL	DATA	COMMENTS
DIMENSIONAL STABILITY TO WASHING	X			
COLOURFASTNESS TO RUBBING	X			
TEAR PROPERTIES OF FABRICS: BALLISTIC PENDULUM METHOD (ELMENDORF)	X			
THREAD COUNT OF WOVEN FABRIC			X	SEE RESULTS
LINEAR DENSITY OF YARN REMOVED FROM WOVEN FABRIC			X	SEE RESULTS

**BUREAU VERITAS CONSUMER PRODUCTS SERVICES (INDIA) PVT. LTD.**

**AUTHORIZED SIGNATORIES**

**APPROVED BY**

**DHINU. DAS**

**DY. PROGRAM MANAGER**

Remark:

See enclosed worksheet for tests result

PLEASE CONTACT:

FOR ANY TECHNICAL ISSUES: **MR. DHINU.DAS**

E. MAIL: [dhinu.das@in.bureauveritas.com](mailto:dhinu.das@in.bureauveritas.com) PHONE NO: 080-40701600/623

FOR ANY INVOICING MATTER: SUNESH G NAIR

E. MAIL: [sunesh.nair@in.bureauveritas.com](mailto:sunesh.nair@in.bureauveritas.com) PHONE NO: 080-40701621



<u>TEST PROPERTY</u>	<u>TEST RESULTS</u>	<u>REQUIREMENTS</u>
<b><u>DIMENSIONAL STABILITY TO WASHING</u></b> (ISO 6330-2012, TYPE: B (MODIFIED), MACHINE WASH PROGRAM AT 30°C±3°C, TUMBLE DRY LOW, AFTER THREE WASH, MACHINE USED: IFB, DETERGENT: SURF EXCEL MATIC)		
	DIMENSIONAL CHANGE (%)	
LENGTH	-0.4%	-3.0 TO +3.0 %
WIDTH	-1.6%	-3.0 TO +3.0 %
(+) EXTENSION	(-) SHRINKAGE	
<b><u>COLOURFASTNESS TO RUBBING</u></b> (BS EN ISO 105-X12:2016 OPTION 2)		
DRY	4-5	MIN. GRADE 3-4
WET	4-5	MIN. GRADE 2-3
<b><u>TEAR PROPERTIES OF FABRICS: BALLISTIC PENDULUM METHOD (ELMENDORF)</u></b> (BS EN ISO 13937-1:2000)		
ACROSS WARP (g)	4326.4	MIN. 800.0 g
ACROSS WEFT (g)	3635.2	MIN. 700.0 g
<b><u>THREAD COUNT OF WOVEN FABRIC</u></b> (ISO 7211/2)		
ENDS/INCH)	160	DATA /
PICK/INCH)	72	/
<b><u>LINEAR DENSITY OF YARN REMOVED FROM WOVEN FABRIC</u></b> (BS ISO 7211-5)		
WARP	75.5 D	+/- 5% /
WEFT	148.5 D	/
<b>COLOURFASTNESS RATING</b>		
GRADE 5	NEGLIGIBLE OR NO CHANGE OR STAINING	
GRADE 4	SLIGHTLY CHANGED OR STAINED	
GRADE 3	NOTICEABLY CHANGED OR STAINED	
GRADE 2	CONSIDERABLY CHANGED OR STAINED	
GRADE 1	MUCH CHANGED OR STAINED	

---End of Report---