

# PASS

**SUBMITTER**

Master Creation

Shop No.70-A Ground Floor, Ward No.418/A, Millenium Textile Market-2, Ring Road, Surat, Gujarat, 395002, India



Report Number  
(8720)277-0446

**STYLE  
NUMBER**

CARIBBEAN SEA IRREGULAR POLKA PRINT

**PRODUCT  
DESCRIPTION**

100% POLYESTER POLY DRUM CREPE

**EXECUTIVE  
SUMMARY**

The submitted sample(s) MEET all the tested requirement(s).

**REMARKS**

/

**TECHNICAL  
QUESTIONS**

Vijith K P  
Directline +91-080-40701600.Ext:684  
[vijith.kp@in.bureauveritas.com](mailto:vijith.kp@in.bureauveritas.com)

**SIGNATURES**

Bureau Veritas Consumer Products Services (I) Pvt Ltd



**GENERAL  
INFORMATION**

Pradipta Kr. Lenka  
Directline +91-080-40701600.Ext:632  
[pradipta.kumar@in.bureauveritas.com](mailto:pradipta.kumar@in.bureauveritas.com)

Vijith K P  
Program Manager  
Softlines Department

**Note:** The submitted samples were not drawn by the laboratory



BUREAU  
VERITAS

Test Report: (8720)277-0446  
MYNTRA JABONG INDIA (P) LTD

Received Date: October 03, 2020

Report Date: October 07, 2020

BRAND	Mast & Harbour
TEST ITEM	Fabric
SAMPLE QUANTITY	2MTR
COLOUR	CARIBBEAN SEA
STYLE REFERENCE NO.	MH-W-AW20-PM-DRESS-105 B
COUNTRY OF ORIGIN	INDIA
FABRIC MILL NAME	K.N.DESIGNER
MANUFACTURER	K.N.DESIGNER
ORDER/PO NO.	N/A
PI / PO NO.	/
FABRIC CONSTRUCTION	10%% POLYESTER
SEASON	AW20
FABRIC WEIGHT	95 GSM
WOVEN OR KNITS OR DENIM	Woven
DIVISION/DEPARTMENT	Women's
TOPS OR BOTTOM	Dresses
COUNTRY OF DESTINATION	INDIA
END USE	WOMEN'S WEAR
YARN COUNT	N/A
SIZE	N/A
AGE RANGE	N/A
TYPE OF FINISH/DYE	PRINT
TYPE OF PRINT	DIGITAL PRINT
SOLE MATERIAL	/
ORDER QUANTITY	366 MTR
ADDITIONAL INFORMATION	/
SUBMITTED FIBER CONTENT	100% POLYESTER
ACTUAL FIBER CONTENT	/
SUGGESTED FIBER CONTENT	/



BUREAU  
VERITAS

Test Report: (8720)277-0446  
MYNTRA JABONG INDIA (P) LTD

Received Date: October 03, 2020

Report Date: October 07, 2020

SUBMITTED CARE INSTRUCTION(S)	MACHINE WASH COLD, TUMBLE DRY LOW.
CLIENT EXPECTED CARE INSTRUCTION	/
SUGGESTED CARE INSTRUCTION(S)	/
RANGE	/
GENDER	/
VENDOR ARTICLE NO.	/
PROTOCOL NUMBER	MYNT-SL-PTCL-00301-IND-WOVEN FABRIC DENIM FABRIC-V9
PROTOCOL STAR LEVEL	/
FAIL RETEST	NO
PREVIOUS REPORT NUMBER	/
RETEST SAMPLE NUMBER	/
FABRIC REPORT NUMBER	/
REPORT EXPIRATION DATE	/



**BUREAU  
VERITAS**

# Test Report: (8720)277-0446 MYNTRA JABONG INDIA (P) LTD

Received Date: October 03, 2020

Report Date: October 07, 2020

## TEST RESULTS FOR 100% POLYESTER POLY DRUM CREPE

TESTED PROPERTY	REQUIREMENTS	RESULTS	RATING
Linear Density of Yarn Removed from Woven Fabric (ISO 7211-5:1984)			
100% Polyester Poly Drum Crepe			DATA
warp (D)	MYNT-SL-301-IND-V9 -5 to 5 %	71.7"D	
weft (D)		92.7"D	
Fabric count of woven fabric (ASTM D3775-17e1)			
100% Polyester Poly Drum Crepe			DATA
Ends	MYNT-SL-301-IND-V9 Provide test results. No PASS/FAIL comment.  ( As Claim (N/A))	128 per inch	
Picks		90 per inch	
Dimensional Changes of Fabrics in Washing (ISO 3759:2011 / ISO 5077:2007 / ISO 6330:2012 (Mod))###			
3N, TUMBLE DRY LOW, 3 MACHINE WASHES			PASS
100% Polyester Poly Drum Crepe			
		Dimensional Change(%)	
Lengthwise	Dimensional Change -3 to 3 %	-0.2	
Widthwise	Dimensional Change -3 to 3 %	0.4	
Tear properties of fabrics: Ballistic Pendulum Method (Elmendorf) (ISO 13937-1:2000)			
100% Polyester Poly Drum Crepe			PASS
Across Warp	MYNT-SL-301-IND-V9 Min. 800 gf	1497.6 gf	
Across Weft	Min. 700 gf	1638.4 gf	
Colourfastness to rubbing (ISO 105-X12:2016)			
100% Polyester Poly Drum Crepe			PASS
Colour Staining - Dry	MYNT-SL-301-IND-V9 Min. Grade 3-4	Grade 4-5	
Colour Staining - Wet	Min. Grade 2-3	Grade 4-5	



**BUREAU  
VERITAS**

# Test Report: (8720)277-0446 MYNTRA JABONG INDIA (P) LTD

Received Date: October 03, 2020

Report Date: October 07, 2020

## TEST RESULTS FOR 100% POLYESTER POLY DRUM CREPE

TESTED PROPERTY	REQUIREMENTS	RESULTS	RATING
-----------------	--------------	---------	--------

### Colourfastness to washing (AATCC 61-13 / SASO ISO 105-C10:2006)###

<b>100% Polyester Poly Drum Crepe</b>			PASS
Colour Change	MYNT-SL-301-IND-V9 Min. Grade 4	Grade 4	
Self Staining	/	Grade 4-5	
Colour Staining on Acetate	Min. Grade 3-4	Grade 4-5	
Colour Staining on Cotton		Grade 4-5	
Colour Staining on Polyamide		Grade 4-5	
Colour Staining on Polyester		Grade 4-5	
Colour Staining on Acrylic		Grade 4-5	
Colour Staining on Wool		Grade 4-5	

### Colorfastness Rating

Color Change	Color Stain / Self Staining
5 - Negligible or No Change	5 - Negligible or No Staining
4 - Slightly Changed	4 - Slightly Stained
3 - Noticeably Changed	3 - Noticeably Stained
2 - Considerably Changed	2 - Considerably Stained
1 - Much Changed	1 - Heavily Stained

### Non-accredited test under NABL scope

END OF REPORT