# PASS

| | |
|---|---|
| **SUBMITTER** | Khurana Sons<br>D- 15/4, Okhla Industrial Area, Phase -Ii, New Delhi, Delhi, India |



Report Number
(6720)322-0745

| | |
|---|---|
| **STYLE NUMBER** | / |
| **PRODUCT DESCRIPTION** | poly gentlemen, Red Ochre |
| **EXECUTIVE SUMMARY** | The submitted sample(s) MEET all the tested requirement(s). |
| **REMARKS** | / |

| | | | |
|---|---|---|---|
| **TECHNICAL QUESTIONS** | RAVINDER KUMAR<br>Directline: +91-0120-4368257<br>Email: ravinder.kumar@in.bureauveritas.com | **SIGNATURES** | Bureau Veritas Consumer Products Services (India) Pvt Ltd. |
| **GENERAL INFORMATION** | HEEMANSHU RATRA<br>Directline: **+**91 9205689949<br>Email: Heemanshu.ratra@in.bureauveritas.com | | RAVINDER KUMAR<br>ASST. PROGRAM MANAGER (SOFTLINE) |

| | |
|---|---|
| **BRAND** | dressberry |
| **TEST ITEM** | Fabric |
| **SAMPLE QUANTITY** | 1.5 mtr |
| **COLOUR** | Red Ochre |
| **STYLE REFERENCE NO.** | DB_SS21_W_TO_AJOD08_02-A |
| **COUNTRY OF ORIGIN** | INDIA |
| **FABRIC MILL NAME** | Rasayan Lifestyle Pvt Ltd. |
| **MANUFACTURER** | / |
| **ORDER/PO NO.** | / |
| **PI / PO NO.** | / |
| **FABRIC CONSTRUCTION** | 100% Poly |
| **SEASON** | ss21 |
| **FABRIC WEIGHT** | / |
| **WOVEN OR KNITS OR DENIM** | Woven |
| **DIVISION/DEPARTMENT** | Women's |
| **TOPS OR BOTTOM** | Dresses |
| **COUNTRY OF DESTINATION** | INDIA |
| **END USE** | woven |
| **YARN COUNT** | poly/poly |
| **SIZE** | / |
| **AGE RANGE** | / |
| **TYPE OF FINISH/DYE** | / |
| **TYPE OF PRINT** | / |
| **SOLE MATERIAL** | / |
| **ORDER QUANTITY** | 1395 |
| **ADDITIONAL INFORMATION** | / |
| **SUBMITTED FIBER CONTENT** | 100%poly |
| **ACTUAL FIBER CONTENT** | / |
| **SUGGESTED FIBER CONTENT** | / |

| | |
|---|---|
| **SUBMITTED CARE INSTRUCTION(S)** | MACHINE COLD WASH DRY IN SHADE DON'T BLEACH NORMAL IRON |
| **CLIENT EXPECTED CARE INSTRUCTION** | / |
| **SUGGESTED CARE INSTRUCTION(S)** | / |
| **RANGE** | / |
| **GENDER** | / |
| **VENDOR ARTICLE NO.** | / |
| **PROTOCOL NUMBER** | MYNT-SL-PTCL-00301-IND-WOVEN FABRIC DENIM FABRIC-V9 |
| **PROTOCOL STAR LEVEL** | / |
| **FAIL RETEST** | NO |
| **PREVIOUS REPORT NUMBER** | / |
| **RETEST SAMPLE NUMBER** | / |
| **FABRIC REPORT NUMBER** | / |
| **REPORT EXPIRATION DATE** | / |

## TEST RESULTS FOR poly gentlemen

| TESTED PROPERTY | REQUIREMENTS | RESULTS | RATING |
|---|---|---|---|
| **Linear Density of Yarn Removed from Woven Fabric** (ISO 7211-5:1984)### | | | |
| **Red Ochre** | | | DATA |
| warp (D) | MYNT-SL-301-IND-V9 -5 to 5 % | 158.4 D | |
| weft (D) | | 149.3 D | |
| **Fabric count of woven fabric** (ASTM D3775-17e1) | | | |
| **Red Ochre** | | | DATA |
| Ends | MYNT-SL-301-IND-V9 Provide test results. No PASS/FAIL comment. ( As Claim (N/A)) | 116 per inch | |
| Picks | | 70 per inch | |

### Dimensional Changes of Fabrics in Washing (ISO 3759:2011 / ISO 5077:2007 / ISO 6330:2012 (Mod))###

MACHINE WASH AT 30 DEGREE CELSIUS , LINE DRY , AFTER 3 WASH

| | | Dimensional Change(%) | |
|---|---|---|---|
| **Red Ochre** | | | PASS |
| Lengthwise | Dimensional Change -3 to 3 % | -0.6 | |
| Widthwise | Dimensional Change -3 to 3 % | -0.6 | |

### Tear properties of fabrics: Ballistic Pendulum Method (Elmendorf) (ISO 13937-1:2000)

| | | | |
|---|---|---|---|
| **Red Ochre** | | | PASS |
| Across Warp | MYNT-SL-301-IND-V9 Min. 600 gf | 4295.8 gf | |
| Across Weft | Min. 550 gf | 2730.4 gf | |

### Colourfastness to rubbing (ISO 105-X12:2016)

| | | | |
|---|---|---|---|
| **Red Ochre** | | | PASS |
| Colour Staining - Dry | MYNT-SL-301-IND-V9 Min. Grade 3-4 | Grade 4-5 | |
| Colour Staining - Wet | Min. Grade 2-3 | Grade 4-5 | |

### Colourfastness to washing (AATCC 61-13 / SASO ISO 105-C10:2006)###

| | | | |
|---|---|---|---|
| **Red Ochre** | | | PASS |

## TEST RESULTS FOR poly gentlemen

| TESTED PROPERTY | REQUIREMENTS | RESULTS | RATING |
|---|---|---|---|
| Colour Change | MYNT-SL-301-IND-V9<br>Min. Grade 4 | Grade 4 | |
| Colour Staining on Acetate | Min. Grade 3-4 | Grade 4-5 | |
| Colour Staining on Cotton | | Grade 4-5 | |
| Colour Staining on Polyamide | | Grade 4-5 | |
| Colour Staining on Polyester | | Grade 4-5 | |
| Colour Staining on Acrylic | | Grade 4-5 | |
| Colour Staining on Wool | | Grade 4-5 | |

### Colorfastness Rating

| Color Change | Color Stain / Self Staining |
|---|---|
| 5 - Negligible or No Change | 5 - Negligible or No Staining |
| 4 - Slightly Changed | 4 - Slightly Stained |
| 3 - Noticeably Changed | 3 - Noticeably Stained |
| 2 - Considerably Changed | 2 - Considerably Stained |
| 1 - Much Changed | 1 - Heavily Stained |

### Non-accredited test under NABL scope

END OF REPORT