

PASS

SUBMITTER

Ajanta Silk
A-4003-4004, Radha Krishna Logistic Park, Near Bharat Cancer Hospital, Saroli, Surat, Gujarat, 385010, India



**STYLE
NUMBER**

TRIBAL DOTS

**PRODUCT
DESCRIPTION**

POLY MOSS CREPE

**EXECUTIVE
SUMMARY**

The submitted sample(s) MEET all the tested requirement(s).

REMARKS

/

**TECHNICAL
QUESTIONS**

Vijith K P
Directline +91-080-40701600.Ext:684
vijith.kp@in.bureauveritas.com

SIGNATURES

Bureau Veritas Consumer Products Services (I) Pvt Ltd



**GENERAL
INFORMATION**

Pradipta Kr. Lenka
Directline +91-080-40701600.Ext:632
pradipta.kumar@in.bureauveritas.com

Vijith K P
Program Manager
Softlines Department

Note: The submitted samples were not drawn by the laboratory



BUREAU
VERITAS

Test Report: (8720)322-0276
MYNTRA JABONG INDIA (P) LTD

Received Date: November 17, 2020

Report Date: November 19, 2020

| | |
|-------------------------|----------------|
| BRAND | dressberry |
| TEST ITEM | Fabric |
| SAMPLE QUANTITY | 2 MTR |
| COLOUR | YELLOW |
| STYLE REFERENCE NO. | TRIBAL DOTS |
| COUNTRY OF ORIGIN | INDIA |
| FABRIC MILL NAME | AJANTA EXPORTS |
| MANUFACTURER | AJANTHA SILK |
| ORDER/PO NO. | N/A |
| PI / PO NO. | / |
| FABRIC CONSTRUCTION | 100% POLYESTER |
| SEASON | SS-21 |
| FABRIC WEIGHT | 115 GSM |
| WOVEN OR KNITS OR DENIM | Woven |
| DIVISION/DEPARTMENT | Women's |
| TOPS OR BOTTOM | Tops |
| COUNTRY OF DESTINATION | INDIA |
| END USE | WOMEN'S WEAR |
| YARN COUNT | N/A |
| SIZE | N/A |
| AGE RANGE | N/A |
| TYPE OF FINISH/DYE | PRINT |
| TYPE OF PRINT | DISPERSE PRINT |
| SOLE MATERIAL | / |
| ORDER QUANTITY | 1515 MTR |
| ADDITIONAL INFORMATION | / |
| SUBMITTED FIBER CONTENT | 100% POLYESTER |
| ACTUAL FIBER CONTENT | / |
| SUGGESTED FIBER CONTENT | / |



BUREAU
VERITAS

Test Report: (8720)322-0276
MYNTRA JABONG INDIA (P) LTD

Received Date: November 17, 2020

Report Date: November 19, 2020

| | |
|----------------------------------|--|
| SUBMITTED CARE INSTRUCTION(S) | MACHINE WASH COLD TUMBLE DRY LOW |
| CLIENT EXPECTED CARE INSTRUCTION | / |
| SUGGESTED CARE INSTRUCTION(S) | / |
| RANGE | / |
| GENDER | / |
| VENDOR ARTICLE NO. | / |
| PROTOCOL NUMBER | MYNT-SL-PTCL-00501.02-IND-WOVEN FABRIC ADDITIONAL COLOURWAY-V4 |
| PROTOCOL STAR LEVEL | / |
| FAIL RETEST | NO |
| PREVIOUS REPORT NUMBER | (8720)314-0239 |
| RETEST SAMPLE NUMBER | / |
| FABRIC REPORT NUMBER | / |
| REPORT EXPIRATION DATE | / |



**BUREAU
VERITAS**

Test Report: (8720)322-0276 MYNTRA JABONG INDIA (P) LTD

Received Date: November 17, 2020

Report Date: November 19, 2020

TEST RESULTS FOR POLY MOSS CREPE

| TESTED PROPERTY | REQUIREMENTS | RESULTS | RATING |
|-----------------|--------------|---------|--------|
|-----------------|--------------|---------|--------|

Dimensional Changes of Fabrics in Washing (ISO 3759:2011 / ISO 5077:2007 / ISO 6330:2012 (Mod))###

3N, TUMBLE DRY LOW, 3 MACHINE WASHES

PASS

| | | | |
|------------------------|------------------------------|------------------------------|------|
| Poly Moss Crepe | | | PASS |
| | | Dimensional Change(%) | |
| | | | |
| Lengthwise | Dimensional Change -3 to 3 % | 0.2 | |
| Widthwise | Dimensional Change -3 to 3 % | -0.1 | |

Colourfastness to rubbing (ISO 105-X12:2016)

| | | | |
|------------------------|---|-----------|------|
| Poly Moss Crepe | | | PASS |
| Colour Staining - Dry | MYNT-SL-501.02-IND-V4 Min. Grade 3-4 | Grade 4-5 | |
| Colour Staining - Wet | Min. Grade 2-3 | Grade 4-5 | |

Colourfastness to washing (AATCC 61-13 / SASO ISO 105-C10:2006)###

| | | | |
|------------------------------|---------------------------------------|-----------|------|
| Poly Moss Crepe | | | PASS |
| Colour Change | MYNT-SL-501.02-IND-V4 Min. Grade 4 | Grade 4 | |
| Self Staining | / | Grade 4-5 | |
| Colour Staining on Acetate | Min. Grade 3-4 | Grade 4-5 | |
| Colour Staining on Cotton | | Grade 4-5 | |
| Colour Staining on Polyamide | | Grade 4-5 | |
| Colour Staining on Polyester | | Grade 4-5 | |
| Colour Staining on Acrylic | | Grade 4-5 | |
| Colour Staining on Wool | | Grade 4-5 | |

Colorfastness Rating

| | |
|-----------------------------|-------------------------------|
| Color Change | Color Stain / Self Staining |
| 5 - Negligible or No Change | 5 - Negligible or No Staining |
| 4 - Slightly Changed | 4 - Slightly Stained |
| 3 - Noticeably Changed | 3 - Noticeably Stained |
| 2 - Considerably Changed | 2 - Considerably Stained |
| 1 - Much Changed | 1 - Heavily Stained |

Non-accredited test under NABL scope

END OF REPORT