

PASS

SUBMITTER

Master Creation

Shop No.70-A Ground Floor, Ward No.418/A, Millenium Textile Market-2, Ring Road, Surat, Gujarat, 395002, India



Report Number
(8720)266-0166

**STYLE
NUMBER**

120YKWSLD93367

**PRODUCT
DESCRIPTION**

100% POLYESTER POLY DRUM CREPE

**EXECUTIVE
SUMMARY**

The submitted sample(s) MEET all the tested requirement(s).

REMARKS

/

**TECHNICAL
QUESTIONS**

Vijith K P
Directline +91-080-40701600.Ext:684
Vijith.kp@in.bureauveritas.com

SIGNATURES

Bureau Veritas Consumer Products Services (I) Pvt Ltd



**GENERAL
INFORMATION**

Pradipta Kr. Lenka
Directline +91-080-40701600.Ext:632
Pradipta.kumar@in.bureauveritas.com

Vijith K P
Program Manager
Softlines Department



BUREAU
VERITAS

Test Report: (8720)266-0166
MYNTRA JABONG INDIA (P) LTD

Received Date: September 22, 2020

Report Date: September 24, 2020

BRAND	YK
TEST ITEM	Fabric
SAMPLE QUANTITY	2MTR
COLOUR	BLACK
STYLE REFERENCE NO.	YK BLACK FLOER PRINT
COUNTRY OF ORIGIN	INDIA
FABRIC MILL NAME	K.N DESIGNER
MANUFACTURER	K.N.DESIGNER
ORDER/PO NO.	N/A
PI / PO NO.	/
FABRIC CONSTRUCTION	100% POLYESTER
SEASON	AW-20
FABRIC WEIGHT	95 GSM
WOVEN OR KNITS OR DENIM	Woven
DIVISION/DEPARTMENT	Kid's - Girls
TOPS OR BOTTOM	Dresses
COUNTRY OF DESTINATION	INDIA
END USE	WOMEN'S WEAR
YARN COUNT	N/A
SIZE	N/A
AGE RANGE	N/A
TYPE OF FINISH/DYE	PRINT
TYPE OF PRINT	DIGITAL PRINT
SOLE MATERIAL	/
ORDER QUANTITY	600 MTR
ADDITIONAL INFORMATION	/
SUBMITTED FIBER CONTENT	100% POLYESTER
ACTUAL FIBER CONTENT	/
SUGGESTED FIBER CONTENT	/



BUREAU
VERITAS

Test Report: (8720)266-0166
MYNTRA JABONG INDIA (P) LTD

Received Date: September 22, 2020

Report Date: September 24, 2020

SUBMITTED CARE INSTRUCTION(S)	MACHINE WASH COLD TUMBLE DRY LOW
CLIENT EXPECTED CARE INSTRUCTION	/
SUGGESTED CARE INSTRUCTION(S)	/
RANGE	/
GENDER	/
VENDOR ARTICLE NO.	/
PROTOCOL NUMBER	MYNT-SL-PTCL-00301-IND-WOVEN FABRIC DENIM FABRIC-V9
PROTOCOL STAR LEVEL	/
FAIL RETEST	NO
PREVIOUS REPORT NUMBER	/
RETEST SAMPLE NUMBER	/
FABRIC REPORT NUMBER	/
REPORT EXPIRATION DATE	/



**BUREAU
VERITAS**

Test Report: (8720)266-0166 MYNTRA JABONG INDIA (P) LTD

Received Date: September 22, 2020

Report Date: September 24, 2020

TEST RESULTS FOR 100% POLYESTER POLY DRUM CREPE

TESTED PROPERTY	REQUIREMENTS	RESULTS	RATING
Linear Density of Yarn Removed from Woven Fabric (ISO 7211-5:1984)			
100% Polyester Poly Drum Crepe			DATA
warp (D)	MYNT-SL-301-IND-V9 -5 to 5 %	1/76.25'D	
weft (D)		1/101.25'D	
Fabric count of woven fabric (ASTM D3775-17e1)			
100% Polyester Poly Drum Crepe			DATA
Ends	MYNT-SL-301-IND-V9 Provide test results. No PASS/FAIL comment. (As Claim (N/A))	152 per inch	
Picks		90 per inch	
Dimensional Changes of Fabrics in Washing (ISO 3759:2011 / ISO 5077:2007 / ISO 6330:2012 (Mod))###			
3N, TUMBLE DRY LOW, 3 MACHINE WASHES			PASS
100% Polyester Poly Drum Crepe			
		Dimensional Change(%)	
Lengthwise	Dimensional Change -3 to 3 %	-0.1	
Widthwise	Dimensional Change -3 to 3 %	-0.3	
Tear properties of fabrics: Ballistic Pendulum Method (Elmendorf) (ISO 13937-1:2000)			
100% Polyester Poly Drum Crepe			PASS
Across Warp	MYNT-SL-301-IND-V9 Min. 800 gf	1578.7 gf	
Across Weft	Min. 700 gf	874.7 gf	
Colourfastness to rubbing (ISO 105-X12:2016)			
100% Polyester Poly Drum Crepe			PASS
Colour Staining - Dry	MYNT-SL-301-IND-V9 Min. Grade 4	Grade 4-5	
Colour Staining - Wet	Min. Grade 3-4	Grade 4-5	



**BUREAU
VERITAS**

Test Report: (8720)266-0166 MYNTRA JABONG INDIA (P) LTD

Received Date: September 22, 2020

Report Date: September 24, 2020

TEST RESULTS FOR 100% POLYESTER POLY DRUM CREPE

TESTED PROPERTY	REQUIREMENTS	RESULTS	RATING
Colourfastness to washing (AATCC 61-13 / SASO ISO 105-C10:2006)###			
100% Polyester Poly Drum Crepe			PASS
Colour Change	MYNT-SL-301-IND-V9 Min. Grade 4	Grade 4	
Self Staining	/	Grade 4-5	
Colour Staining on Acetate	Min. Grade 3-4	Grade 4-5	
Colour Staining on Cotton		Grade 4-5	
Colour Staining on Polyamide		Grade 4-5	
Colour Staining on Polyester		Grade 4-5	
Colour Staining on Acrylic		Grade 4-5	
Colour Staining on Wool		Grade 4-5	

Colorfastness Rating

Color Change	Color Stain / Self Staining
5 - Negligible or No Change	5 - Negligible or No Staining
4 - Slightly Changed	4 - Slightly Stained
3 - Noticeably Changed	3 - Noticeably Stained
2 - Considerably Changed	2 - Considerably Stained
1 - Much Changed	1 - Heavily Stained

Non-accredited test under NABL scope

END OF REPORT