

MYNTRA JABONG INDIA (P) LTD TEST REPORT

Technical Report: (8719)014-0142

Page 1 of 4 January 17, 2019



Certificate No. TC-6092 (Pls Refer the website www.nabl-inida.org to view the scope of accreditation)



MYNTRA JABONG INDIA (P) LTD TEST REPORT

AJANTA SILK

ATTN: WASIM PINJARA

LAB NO.: (8719)014-0142

 FORM NO.:
 233131

 DATE IN:
 Jan 14, 2019

 DATE OUT:
 Jan 17, 2019

 BRAND:
 DRESSBERRY

NO. OF WORKING DAYS: 03


PAGE 2 OF 4

OVERALL RATING	
PASS	X
FAIL	
DATA	

Vendor:	AJANTA SILK	Agent:	1
Fabric Supplier/Mill:	AJANTA EXPORTS	Factory/Manufacturer:	AJANTA SILK
P.O. No.:	/	Style No.:	GARDEN SPACED
			OUT FLORAL-B
Sample Description:	WOVEN 100% POLYESTER AMERICAN CRAPE FABRIC, SAMPLE RECEIVED IN GOODCONDITION (DEPT:WOMENS)	Style Reference No:	/
Color:	CORAL ALMOND	Country of Origin:	INDIA
Claimed Fabric Weight:	95 GSM	Fabric Construction:	100% POLYESTER MOSS CREPE
Yarn Size:	/	Submitted Size:	/
Season:	SS19	FPU No.:	/
Type of Print:	OVER PRINT	End Use:	WOMENS WEAR

Product Category	WOVEN FABRIC
Test Requested	ADDITIONAL COLOR PACKAGE TEST
Previous Report No.	FULL PKG REPORT# (8719)014-0143

Submitted Fiber	100% POLYESTER
Content	
Actual Fiber Content	
Suggested Fiber	
Content	
Submitted Care	MACHINE WASH COLD, TUMBLE DRY LOW
Instruction(s)	





TEST PROPERTY	PASS	FAIL	DATA	COMMENTS
DIMENSIONAL STABILITY TO WASHING	Χ			
COLOURFASTNESS TO RUBBING	X			

BUREAU VERITAS CONSUMER PRODUCTS SERVICES (INDIA) PVT. LTD. AUTHORIZED SIGNATORIES

APPROVED BY:

VLIITH KP

VIJITH KP ASST. PROGRAM MANAGER

REMARK: See enclosed worksheet for tests result.

PLEASE CONTACT:

FOR ANY TECHNICAL ISSUES: MR.RAJENDRA PRADHAN

E. MAIL: rajendra.pradhan@in.bureauveritas.com PHONE NO: 080-40701628

FOR ANY INVOICING MATTER: SUNESH G NAIR

E. MAIL: <u>Sunesh.nair@in.bureauveritas.com</u> PHONE NO: 080-40701621





TEST RESULTS

TEST PROPERTY REQUIREMENTS

DIMENSIONAL STABILITY TO WASHING (ISO 6330-2012, TYPE:B

(MODIFIED), MACHINE WASH PROGRAM AT 30°C+3°C, TUMBLE DRY LOW, AFTER THREE WASH, MACHINE USED: IFB, DETERGENT: SURF EXCEL MATIC)

DIMENSIONAL CHANGE (%)

LENGTH -0.4% -3.0 TO +3.0 % WIDTH -0.3% -3.0 TO +3.0 %

(-) SHRINKAGE (+) EXTENSION

COLOURFASTNESS TO RUBBING(BS EN ISO 105-X12:2016 OPTION 2)

DRY 4-5 MIN. GRADE 3-4 WET 4 - 5MIN. GRADE 2-3

COLOURFASTNESS RATING

NEGLIGIBLE OR NO CHANGE OR STAINING GRADE 5 GRADE 4 SLIGHTLY CHANGED OR STAINED

GRADE 3 NOTICEABLY CHANGED OR STAINED GRADE 2 CONSIDERABLY CHANGED OR STAINED GRADE 1 MUCH CHANGED OR STAINED

---End of Report---