Highlights

- Paired Monte Carlo tests carbon and durability claims for shell-derived concrete
- Published data reject the inert-filler model; one calibration does not transfer
- Strength efficiency differs between studies, so a pooled distribution is used
- Joint advantage is rare and zero against a 50% slag blended-cement reference
- Durability conclusions depend on an uncalibrated filler-pore coupling