

The Basalt Fibre Spinnery

Drawing Structural Fibre and Rebar Directly from Melted Rock

Concept Study BF-CS-024 · Off-World Civilisation Toolkit, Volume II · July 2026

Classification: Speculative engineering, constrained to known physics

Wijerathne Arachchilage Sandun Priyankara Wijerathne

sandunwijerathne51@gmail.com · linkedin.com/in/sandun-wijerathne · github.com/sandunwijerathne

Abstract

A civilisation cannot be built on ceramic alone. The sintered domes and regolith structures of the companion concepts are strong in compression but brittle, and a growing settlement needs materials that can also carry tension: rebar to reinforce them, cable to hold them, cloth to wrap them, beams that bend before they break. On Earth we make these from steel and from glass and carbon fibre, all of which demand elaborate feedstock chains. This study describes a machine that makes a structural fibre from nothing but rock. The BF-1 'Arachne' melts basaltic regolith and draws the melt through fine openings into continuous filaments that cool into a strong, stiff, temperature-resistant fibre — the off-world equivalent of a steel mill, producing reinforcement, textile, and composite feedstock from the most common rock on the terrestrial planets and the Moon. The process is not speculative: basalt fibre is a mature industrial material on Earth, spun from quarried rock with a single mineral input and no additives. We describe the melt-and-draw process, the products, the pairing with the catalogue's ceramic structures, and the honest energy and equipment challenges of doing it off Earth.

1. Introduction: The Missing Half of a Material Palette

The construction concepts elsewhere in this catalogue share a strength and a weakness. Sintered regolith domes, cast basalt, and fused-soil structures are excellent in compression — they bear crushing loads well, as stone and concrete do — but they are brittle, weak in tension, and prone to sudden failure rather than graceful bending. A settlement built only from such materials would be a settlement of arches and vaults and nothing else: no reinforced spans, no cables, no pressure membranes, no woven cloth, no flexible or tension-bearing components at all. That is not a civilisation's material palette; it is half of one.

On Earth we complete the palette with steel and with manufactured fibres, but both are awkward off-world. Steel-making from lunar or Martian ore is a long, energy-hungry, multi-step chain. Glass and carbon fibres demand refined feedstocks and careful chemistry. What a young off-world industry needs is a tension-bearing structural material that can be made in one step, from a feedstock lying everywhere, with no imported additives. Basalt fibre is exactly that material, and the Spinnery is the machine that makes it.

2. Concept Description

The BF-1 'Arachne' is, in essence, a rock-melting furnace feeding a fibre-drawing head. It gathers basaltic material — the dark, iron- and magnesium-rich volcanic rock that dominates the lunar maria, the Martian surface, and much of Earth — and melts it in a furnace to a glowing, honey-like liquid. That melt is held at a controlled temperature and allowed to flow through an array of fine openings in a heat-resistant plate; as each thread of melt emerges and is drawn away and cooled, it stretches into a thin, continuous filament of solid basalt fibre. Many filaments are gathered together into a strand, which can be

wound onto a spool, chopped for reinforcement, or fed onward into cloth or composite.

The remarkable thing about the process is its simplicity of input. Making conventional glass fibre requires blending several refined ingredients; basalt fibre requires only basalt. The rock already contains, in roughly the right proportions, everything the fibre needs, so the process is genuinely single-feedstock: melt the rock, draw the melt, and the fibre is made, with no additives to import or mix. This is what makes it so well suited to a place where every imported chemical is a burden and the local rock is free.

3. Why Basalt, and Why It Works

Basalt is the most abundant volcanic rock in the inner solar system. It forms the dark lunar maria that are the likely sites of early bases; it covers vast regions of Mars; and it is common across Earth, where basalt fibre is already manufactured at industrial scale. Its suitability for fibre is not a lucky accident but a consequence of its composition: basalt is a silicate rock that, when melted, forms a glass-forming liquid of the right viscosity to be drawn into filaments, and it solidifies into a fibre that is strong in tension, stiff, and notably resistant to heat and chemical attack.

On Earth, basalt fibre is valued precisely for these properties — it is used as reinforcement in concrete and composites, as a high-temperature insulation, and as a competitor to glass fibre, produced from a single quarried mineral feedstock with a comparatively simple melt-and-spin process (Fiore et al., 2015). Its mechanical performance sits broadly in the range of glass fibre, with better temperature tolerance, and its production has been characterised in detail in the materials literature (Dhand et al., 2015). Crucially for off-world use, everything that makes it attractive on Earth — single feedstock, no additives, tolerance of heat, strength in tension — is amplified in a setting where feedstock chains are the main constraint. The Moon and Mars are, in this narrow sense, ideally supplied: they are made largely of the raw material this industry consumes.

4. The Machine and Its Products

The Spinnery's core is thermal. It must reach and hold the melting temperature of basalt — high, but far below what metal-smelting or many ceramics demand — and hold the melt steady while it is drawn, since fibre quality depends on a stable temperature and a stable flow. It needs a furnace, a controlled drawing head with its array of fine openings, a means of pulling and winding the emerging filaments at a steady rate, and a substantial, reliable power supply, since melting rock continuously is fundamentally an energy-intensive act. The drawing head, exposed to molten silicate at high temperature, is the component under the harshest duty and the one whose materials and lifetime most constrain the design.

From that single machine flows a whole family of products. Continuous fibre wound on spools becomes cable, cordage, and the reinforcing yarn for composites. Chopped fibre becomes the reinforcement mixed into sintered or cast regolith to give brittle ceramic the tensile strength it lacks — the direct partner to the dome and cast-basalt concepts, turning their compression-only structures into reinforced ones. Woven fibre becomes cloth for soft structures, insulation, and membranes. Combined with a binder, the fibre becomes a composite for panels and beams. A single feedstock and a single process thus supply the tension-bearing half of the material palette that the catalogue's ceramic concepts cannot provide alone.

Product	Made from	Replaces / enables
---------	-----------	--------------------

Continuous fibre	drawn filament, spooled	cable, cordage, yarn
Chopped fibre	cut filament	rebar for ceramic/regolith
Woven cloth	fibre on a loom	membranes, insulation, soft goods
Composite stock	fibre + binder	panels, beams, shells
Feedstock	basalt only	no additives, no imports

Table 1. One feedstock, one process, a family of products.

5. Operations Concept

Phase one is chopped-fibre reinforcement: the simplest product, mixed into the sintered and cast structures already being built, immediately upgrading brittle compression-only elements into reinforced ones without requiring perfect continuous-filament quality. Phase two is continuous fibre and cable, demanding steadier control of melt and draw, supplying cordage and the yarn for composites and cloth. Phase three is full textile and composite production — woven membranes, composite panels and beams — establishing basalt fibre as the settlement's general-purpose tension material. Throughout, the Spinnery is conceived as the tension-side partner to the compression-side structures of the sinter dome and cast-basalt concepts: together they span the full range from crushing to pulling loads, entirely from local rock.

6. Honest Difficulties

The obstacles are those of any high-temperature industrial process moved off Earth. Energy is foremost: melting rock continuously requires sustained high-temperature heat, which means a large and reliable power supply, whether solar-concentrated or electrical. The drawing head endures the harshest conditions — molten silicate, high temperature, continuous flow — and its materials, lifetime, and replacement are a genuine engineering problem, as it is on Earth. Feedstock composition varies from place to place, and a rock richer or poorer in certain oxides will melt and draw differently, so the process must sense and adapt rather than follow a fixed recipe (Dhand et al., 2015). Fine glassy fibres bring a handling and health hazard that must be managed, particularly in an enclosed habitat. And doing precision fibre-drawing in low gravity, vacuum, and dust is unproven at scale, however mature the terrestrial process. None of these is a barrier of physics; basalt fibre is an existing industrial material (Fiore et al., 2015). They are the ordinary, solvable difficulties of building a factory somewhere hard.

7. Pathway to Reality

This concept rests on an unusually solid foundation, because the product already exists and is manufactured commercially. Basalt fibre is produced on Earth today from quarried rock, its properties and processing are documented in the materials-science literature (Fiore et al., 2015; Dhand et al., 2015), and the melt-and-draw method is well understood. What must be developed is not the material but its off-world production: melting local basalt with in-situ power, operating a drawing head reliably in the surface environment, and adapting to variable feedstock. The credible near-term step is the chopped-fibre reinforcement plant — a lower-precision product that immediately strengthens the structures being built by the companion concepts — with continuous fibre and textiles following as the process is refined. Because it directly complements the catalogue's ceramic construction, the Spinnery is a natural second industry for any settlement that has learned to sinter its regolith.

8. Conclusion

Stone builds well in compression and fails in tension, and every builder since the first arch has needed something to supply what stone cannot. On Earth we reached for iron; off Earth, the answer may be the stone itself, melted and redrawn into thread. The Basalt Fibre Spinnery turns the most common rock of the inner solar system into cable, cloth, and reinforcement in a single step with no imported ingredient, completing the material palette that the catalogue's ceramic structures begin. It is a steel mill for worlds with no iron industry — and, like the best of these concepts, it works not because of any new discovery but because the ground beneath a future settlement is already made, almost entirely, of the one thing the machine needs to be fed.

References

Harvard referencing style (Cite Them Right).

Dhand, V., Mittal, G., Rhee, K.Y., Park, S.-J. and Hui, D. (2015) 'A short review on basalt fiber reinforced polymer composites', *Composites Part B: Engineering*, 73, pp. 166-180.

Fiore, V., Scalici, T., Di Bella, G. and Valenza, A. (2015) 'A review on basalt fibre and its composites', *Composites Part B: Engineering*, 74, pp. 74-94.