

# popoff: POtential Parameter Optimisation for Force-Fields

Lucy M. Morgan<sup>1, 2</sup>, Matt J. Clarke<sup>1</sup>, M. Saiful Islam<sup>1, 2</sup>, and Benjamin J. Morgan<sup>1, 2</sup>

<sup>1</sup> Department of Chemistry, University of Bath, Claverton Down, UK, BA2 7AY <sup>2</sup> The Faraday Institution, Quad One, Harwell Campus, Didcot, OX11 0RA, UK

DOI: [10.21105/joss.03451](https://doi.org/10.21105/joss.03451)

## Software

- [Review](#) ↗
- [Repository](#) ↗
- [Archive](#) ↗

Editor: [Pending Editor](#) ↗

Submitted: 02 July 2021

Published: 04 July 2021

## License

Authors of papers retain copyright and release the work under a Creative Commons Attribution 4.0 International License ([CC BY 4.0](#)).

## Summary

PopOff is a Python package for fitting Coulomb-Buckingham type interatomic potentials for classical potential-based molecular dynamics (MD). This is a modular fitting code, allowing increased control over several important aspects of the potential. Formal charge, partial charge, or a charge scaling factor can be fitted. A rigid ion model, a core-shell model, or mixture of both can be chosen. If choosing to fit a core-shell model, the charge separation over the core and shell components can be fixed or fitted, as can the spring constant. Individual Buckingham parameters can also be selectively fixed, fitted, or set to zero. PopOff currently fits to first principles derived forces and stress tensors obtained from a VASP training set through the `vasprun.xml` output files. The LAMMPS MD code is used as a backend to perform the MD during the fitting process.

The development of sufficiently accurate interatomic potentials, which requires model parameterization with respect to a set of target observables, for a specific chemistry is quite challenging, especially for complex systems. For example, in layered structures, such as the widely used  $\text{LiNiO}_2$  based cathode materials, the short-range interactions are overwhelmed by the longer-range Coulombic term. In these cases, the system charges need to be scaled down to increase the influence of the short-range interactions, termed as partial charges, and the influence of polarizability needs to be included, usually through using a core-shell model. Variations of the Buckingham potential have been developed for these systems, some using rigid ion models, (Dawson & Tanaka, 2014; Ledwaba et al., 2020; Lewis & Catlow, 1985; Sayle et al., 2005) and others using core-shell models, (Ammundsen et al., 1999; Fisher et al., 2010; Hart & Bates, 1998; He et al., 2019; Kerisit et al., 2014; Lee & Park, 2012; Lewis & Catlow, 1985) with a mixture of formal and partial charges being used. Interatomic potentials are traditionally based on mathematical functions which have been parameterized using experimental and/or First Principles derived data (Buckingham, 1938; Jones, 1924). There are a limited number of codes available with the explicit purpose or functionality for fitting potentials. Fitting routines from established codes including the General Utility Lattice Program (GULP), (Gale, 1997) Atomicrex, (Stukowski et al., 2017) dftfit, (Ostrouchov, n.d.) and potfit (Wen et al., 2017) each possess unique functionality, however, none are fully able to produce robust potentials for NMC or  $\text{LiNiO}_2$  due to different aspects not being considered within the code, such as charge scaling or core-shell models. PopOff has been specifically developed for fitting different permutations of the Buckingham potential. Its modular design allows flexible fitting of both rigid ion and core-shell models, and formal and partial charges.

We are currently using PopOff in our own research to develop potentials for cathode and solid-electrolyte materials for classical MD analysis of  $\text{Li}^+/\text{Na}^+$  migration properties. PopOff is also being used by a group at Newcastle University to develop potentials for several halide based solid-electrolyte materials in collaboration with experimental partners. We hope that this

open-source resource will support development of interatomic potentials tailored to individual systems, and thus results in better approximations of the atomic interactions.

## Statement of need

Interatomic potentials give an approximate mathematical description of the interactions between atoms in a given system. These interactions are unique to the species and the surrounding environment, yet in the wider literature interatomic potentials between specific atom types, for example Li-O, are reused in vastly different systems. This is particularly familiar for the O-O potential derived by Jackson and Catlow in 1985 for  $\text{UO}_2$ , (Jackson & Catlow, 1985) which has since been used in the study of many materials, in particular ionic solids. Although in some cases the species interactions may not vary substantially between different materials, in other cases it does, and to varying degrees. For example, a particular metal-oxygen interaction in a spinel might be considerably different to that in a layered oxide material, due in part to the charge distribution increasing the influence of polarizability. It is therefore crucial to develop interatomic potentials for individual systems to get the best approximation of the interactions within that environment.

There are a limited number of codes available with the explicit purpose or functionality for fitting potentials. Most of which require some pre-requisite knowledge of coding or specialism, creating a prohibitive barrier for utilising these tools in the wider atomistic modelling research community. These codes are also not able to account for all aspects which may need to be considered for particular materials, such as polarizability. Creating a resource, with minimal pre-requisite requirements to use, and able to account for a larger range of material considerations needed for accurate potentials is therefore key to producing more robust classical MD investigations.

## Optimiser

PopOff uses `scipy.optimize.differential_evolution` as its global optimiser to optimise the function that calculates the mean squared error between the forces and stress tensors within the training set and those calculated with possible classical MD potentials, via:

$$\chi^2 = \frac{1}{n} \sum_{i=1}^n (Y_i - \hat{Y}_i)^2$$

where  $n$  is the number of data points,  $Y_i$  is the observed values, and  $\hat{Y}_i$  is the predicted values.

Differential evolution is a stochastic population-based method, where at each pass through the population the algorithm mutates each candidate solution by mixing with other candidate solutions to create a trial candidate. There are several strategy methods which can be used to create the trial candidate, with `latinhypercube` used as default.

PopOff's modular design allows the code to fit the following parameters:

- A rigid ion model, a core-shell model, or mixture of both.
- For a core-shell model, the charge separation over the core and shell components can be fixed or fitted as can the spring constant.
- Selectively fix, fit, or set to zero the individual Buckingham parameters.

## Approximations and Limitations

- Due to the different orders of magnitude between the forces acting on the atoms and the stress tensors of the system, the stress tensors are scaled by \*0.001 to give higher weighting to the forces. This can be changed in `fitting_code.py`, however, this is not given as a suggested change in the manual.
- Care needs to be taken in choosing the cutoff value, which must be less than half minimum cell width to prevent self interactions. This value is set as 10 Angstroms as default and can be changed in the `fitting_code.py`, however, this is not given as a suggested change in the manual.

## Acknowledgements

L. M. M. acknowledges support from the Faraday Institution (faraday.ac.uk; EP/S003053/1: Grant No. FIRG003). Additional support was received from the Royal Society (UF130329, URF\R\191006).

## References

- Ammundsen, B., Burns, G. R., Islam, M. S., Kanoh, H., & Rozière, J. (1999). Lattice Dynamics and Vibrational Spectra of Lithium Manganese Oxides: A Computer Simulation and Spectroscopic Study. *The Journal of Physical Chemistry B*, 103(25), 5175–5180. <https://doi.org/10.1021/jp984398l>
- Buckingham, R. A. (1938). The classical equation of state of gaseous helium, neon and argon. *Proceedings of the Royal Society of London. Series A. Mathematical and Physical Sciences*, 168(933), 264–283. <https://doi.org/10.1098/rspa.1938.0173>
- Dawson, J. A., & Tanaka, I. (2014). Oxygen Vacancy Formation and Reduction Properties of  $\beta$ -MnO<sub>2</sub> Grain Boundaries and the Potential for High Electrochemical Performance. *ACS Applied Materials & Interfaces*, 6(20), 17776–17784. <https://doi.org/10.1021/am504351p>
- Fisher, C. A. J., Islam, M. S., & Moriwake, H. (2010). Atomic Level Investigations of Lithium Ion Battery Cathode Materials. *Journal of the Physical Society of Japan*, 79(Suppl.A), 59–64. <https://doi.org/10.1143/JPSJS.79SA.59>
- Gale, J. D. (1997). GULP: A computer program for the symmetry-adapted simulation of solids. *Journal of the Chemical Society, Faraday Transactions*, 93(4), 629–637. <https://doi.org/10.1039/a606455h>
- Hart, F. X., & Bates, J. B. (1998). Lattice model calculation of the strain energy density and other properties of crystalline LiCoO<sub>2</sub>. *Journal of Applied Physics*, 83(12), 7560–7566. <https://doi.org/10.1063/1.367521>
- He, J., Zhang, L., & Liu, L. (2019). Thermal transport in monocrystalline and polycrystalline lithium cobalt oxide. *Physical Chemistry Chemical Physics*, 21, 12192–12200. <https://doi.org/10.1039/C9CP01585J>
- Jackson, R. A., & Catlow, C. R. A. (1985). Trapping and solution of fission Xe in UO<sub>2</sub>.: Part 1. Single gas atoms and solution from underpressurized bubbles. *Journal of Nuclear Materials*, 127(2-3), 161–166.
- Jones, J. E. (1924). On the determination of molecular fields. -II. From the equation of state of a gas. *Proceedings of the Royal Society of London. Series A, Containing Papers of a*

- 123 *Mathematical and Physical Character*, 106(738), 463–477. [https://doi.org/10.1098/rspa.](https://doi.org/10.1098/rspa.1924.0082)  
124 [1924.0082](https://doi.org/10.1098/rspa.1924.0082)
- 125 Kerisit, S., Chaka, A. M., Droubay, T. C., & Ilton, E. S. (2014). Shell Model for Atom-  
126 istic Simulation of Lithium Diffusion in Mixed Mn/Ti Oxides. *The Journal of Physical*  
127 *Chemistry C*, 118(42), 24231–24239. <https://doi.org/10.1021/jp506025k>
- 128 Ledwaba, R. S., Sayle, D. C., & Ngoepe, P. E. (2020). Atomistic Simulation and Characteri-  
129 zation of Spinel  $\text{Li}_{1+x}\text{Mn}_2\text{O}_4$  ( $0 \leq x \leq 1$ ) Nanoparticles. *ACS Applied Energy Materials*,  
130 3(2), 1429–1438. <https://doi.org/10.1021/acsaem.9b01870>
- 131 Lee, S., & Park, S. S. (2012). Atomistic simulation study of mixed-metal oxide  
132 ( $\text{LiNi}_{1/3}\text{Co}_{1/3}\text{Mn}_{1/3}\text{O}_2$ ) cathode material for lithium ion battery. *The Journal of*  
133 *Physical Chemistry C*, 116(10), 6484–6489.
- 134 Lewis, G. V., & Catlow, C. R. A. (1985). Potential models for ionic oxides. *Journal of Physics*  
135 *C: Solid State Physics*, 18(6), 1149–1161. <https://doi.org/10.1088/0022-3719/18/6/010>
- 136 Ostrouchov, C. (n.d.). *dffit*. Retrieved September 29, 2020, from [https://chrisostrouchov.](https://chrisostrouchov.com/dffit)  
137 [com/dffit](https://chrisostrouchov.com/dffit)
- 138 Sayle, T. X. T., Catlow, C. R. A., Maphanga, R. R., Ngoepe, P. E., & Sayle, D. C. (2005).  
139 Generating  $\text{MnO}_2$  Nanoparticles Using Simulated Amorphization and Recrystallization.  
140 *Journal of the American Chemical Society*, 127(37), 12828–12837. [https://doi.org/10.](https://doi.org/10.1021/ja0434073)  
141 [1021/ja0434073](https://doi.org/10.1021/ja0434073)
- 142 Stukowski, A., Fransson, E., Mock, M., & Erhart, P. (2017). Atomicrex—a general purpose tool  
143 for the construction of atomic interaction models. *Modelling and Simulation in Materials*  
144 *Science and Engineering*, 25(5), 055003. <https://doi.org/10.1088/1361-651x/aa6ecf>
- 145 Wen, M., Li, J., Brommer, P., Elliott, R. S., Sethna, J. P., & Tadmor, E. B. (2017). A  
146 KIM-compliant *potfit* for fitting sloppy interatomic potentials: application to the EDIP  
147 model for silicon. *Modelling and Simulation in Materials Science and Engineering*, 25(1),  
148 014001. <https://doi.org/10.1088/0965-0393/25/1/014001>