


# Compression India Pvt Ltd

Thane Belapur MIDC Near BandraKurla Complex, A-Wing , Plot No 202 , MG Road, Pin 400556

|                   |                           |                |                     |
|-------------------|---------------------------|----------------|---------------------|
| Tested Date:      | 2023-03-08 17:14:16       | Test No:       | 25                  |
| Job Name :        | jghgj                     | Batch ID:      | fdfdgfdg            |
| Specimen Name:    | Rubber                    | Specmen Shape: | Rectangle           |
| Test Type:        | Tensile                   | Specmen Specs: | 25                  |
| Party Name :      | MRF                       | Motor Speed :  | 500                 |
| Guage Length(mm): | 320                       | Report Date:   | 2023-03-08 17:15:10 |
| Tested By :       | Sanjay Mane [SUPER_ADMIN] |                |                     |



| Spec. No. | Thickness (cm) | Width (cm) | CS.Area (cm2) | Force at Peak (kgf) | E@Peak (cm) | % E@Peak | E@Break (cm) | %E@Break |
|-----------|----------------|------------|---------------|---------------------|-------------|----------|--------------|----------|
| 1         | 0.26           | 0.61       | 0.1586        | 339.10              | 3.96        | 12.37    | 4.18         | 13.06    |
| 2         | 0.26           | 0.61       | 0.1586        | 310.80              | 5.28        | 16.50    | 5.28         | 16.50    |
| 3         | 0.26           | 0.61       | 0.1586        | 268.30              | 3.82        | 11.94    | 3.98         | 12.44    |
| 4         | 0.26           | 0.61       | 0.1586        | 209.10              | 4.60        | 14.00    | 4.88         | 15.25    |
| AVG       | 0.26           | 0.61       | 0.1586        | 281.82              | 4.42        | 13.70    | 4.58         | 14.31    |
| MAX       | 0.26           | 0.61       | 0.1586        | 339.10              | 5.28        | 16.50    | 5.28         | 16.50    |
| MIN       | 0.26           | 0.61       | 0.1586        | 209.10              | 3.82        | 11.94    | 3.98         | 12.44    |

| Spec. No | TensileStrength (Kgf/Cm2) | Mod@100% (Kgf/Cm2) | Mod@200% (Kgf/Cm2) | Mod@300% (Kgf/Cm2) |
|----------|---------------------------|--------------------|--------------------|--------------------|
| 1        | 2138.08                   | 0.00               | 0.00               | 0.00               |
| 2        | 1959.65                   | 0.00               | 0.00               | 0.00               |
| 3        | 1691.68                   | 0.00               | 0.00               | 0.00               |
| 4        | 1318.41                   | 0.00               | 0.00               | 0.00               |
| AVG      | 1776.95                   | 0.00               | 0.00               | 0.00               |
| MAX      | 2138.08                   | 0.00               | 0.00               | 0.00               |

|     |         |      |      |      |
|-----|---------|------|------|------|
| MIN | 1318.41 | 0.00 | 0.00 | 0.00 |
|-----|---------|------|------|------|

Remark : None

Authorised and Signed By : \_\_\_\_\_.