


Stech Engineers

Office Address Here

Tested Date:	2023-02-25 12:14:28	Test No:	12
Job Name :	tear	Batch ID:	tearbatch
Specimen Name:	Rubber	Specmen Shape:	Rectangle
Test Type:	Tear	Specmen Specs:	12
Party Name :	MRF	Motor Speed :	500
Guage Length(mm):	320	Report Date:	2023-02-25 12:15:12
Tested By :	Stech engineers testing machine		



Spec. No	Thickness (cm)	Force at Peak (Kgf)	Tear Strength (Kgf/cm)
1	0.26	65.60	252.31
2	0.26	70.70	271.92
3	0.26	65.00	250.00
4	0.26	75.00	288.46
AVG	0.26	69.07	265.67
MAX	0.26	75.00	288.46
MIN	0.26	65.00	250.00

Remark : None

Authorised and Signed By : _____.