


Compression India Pvt Ltd

Thane Belapur MIDC Near BandraKurla Complex, A-Wing , Plot No 202 , MG Road, Pin 400556

Tested Date:	2023-03-08 12:57:51	Test No:	19
Job Name :	dfgdfg	Batch ID:	fdgdfg
Specimen Name:	Rubber	Specmen Shape:	Rectangle
Test Type:	Tensile	Specmen Specs:	19
Party Name :	MRF	Motor Speed :	500
Guage Length(mm):	320	Report Date:	2023-03-08 17:05:36
Tested By :			



Spec. No.	Thickness (cm)	Width (cm)	CS.Area (cm2)	Force at Peak (kgf)	E@Peak (cm)	% E@Peak	E@Break (cm)	%E@Break
1	0.26	0.61	0.1586	331.60	3.99	12.47	4.20	13.00
2	0.26	0.61	0.1586	384.10	5.27	16.47	6.32	19.75
3	0.26	0.61	0.1586	329.10	4.44	13.88	4.81	15.03
4	0.26	0.61	0.1586	165.80	0.09	0.28	0.09	0.28
5	0.26	0.61	0.1586	306.60	3.93	12.28	4.62	14.44
AVG	0.26	0.61	0.1586	303.44	3.54	11.07	4.01	12.50
MAX	0.26	0.61	0.1586	384.10	5.27	16.47	6.32	19.75
MIN	0.26	0.61	0.1586	165.80	0.09	0.28	0.09	0.28

Spec. No	TensileStrength (Kgf/Cm2)	Mod@100% (Kgf/Cm2)	Mod@200% (Kgf/Cm2)	Mod@300% (Kgf/Cm2)	Mod@100% (Kgf/Cm2)
1	2090.79	0.00	0.00	0.00	0.00
2	2421.82	0.00	0.00	0.00	0.00
3	2075.03	0.00	0.00	0.00	0.00
4	1045.40	0.00	0.00	0.00	0.00
5	1933.17	0.00	0.00	0.00	0.00

AVG	1913.24	0.00	0.00	0.00	0.00
MAX	2421.82	0.00	0.00	0.00	0.00
MIN	1045.40	0.00	0.00	0.00	0.00

Remark : None

Authorised and Signed By : _____.