


Asian Test Equipments

Office Address Here

Tested Date:	2023-02-15 13:13:33	Test No:	2
Job Name :	test2	Batch ID:	batch2
Specimen Name:	Rubber	Specmen Shape:	Rectangle
Test Type:	Tensile	Specmen Specs:	2
Party Name :	MRF	Motor Speed :	500
Guage Length(mm):	320	Report Date:	2023-02-15 13:14:27
Tested By :			



Spec. No.	Thickness (cm)	Width (cm)	CS.Area (cm2)	Force at Peak (kgf)	E@Peak (cm)	% E@Peak	E@Break (cm)	%E@Break
1	0.26	0.61	0.1586	103.40	0.00	0.00	0.00	0.00
2	0.26	0.61	0.1586	66.40	3.66	11.44	4.03	12.59
3	0.26	0.61	0.1586	75.50	2.16	6.75	2.58	8.06
4	0.26	0.61	0.1586	67.80	4.73	14.78	4.73	14.78
AVG	0.26	0.61	0.1586	78.28	2.64	8.24	2.84	8.86
MAX	0.26	0.61	0.1586	103.40	4.73	14.78	4.73	14.78
MIN	0.26	0.61	0.1586	66.40	0.00	0.00	0.00	0.00

Spec. No	TensileStrength (Kgf/Cm2)	Mod@100% (Kgf/Cm2)	Mod@200% (Kgf/Cm2)	Mod@300% (Kgf/Cm2)
1	651.95	0.00	0.00	0.00
2	418.66	0.00	0.00	0.00
3	476.04	0.00	0.00	0.00
4	427.49	0.00	0.00	0.00
AVG	493.54	0.00	0.00	0.00
MAX	651.95	0.00	0.00	0.00

MIN	418.66	0.00	0.00	0.00
-----	--------	------	------	------

Remark : None

Authorised and Signed By : _____.