EXPERIMENTAL FACT	OUR VERDICT	WHY IT FOLLOWS
Anhydrous (5.5 Å) is not SC *Foo 2003*	explained	$\alpha > 0$: single stiff well ($\hbar\omega \approx 30$ meV), $N(0) \approx 0$ — no 2DEG, nothing to pair.
Monolayer hydrate (6.9 Å) is not SC *Foo 2003*	explained	Past the window: $\lambda \approx 20 \gg 2$ — the alkali self-traps (polaronic), so SC is killed.
Bilayer hydrate (9.9 Å) is SC, T_c=4.5 K *Takada 2003*	prediction	Bare geometry is polaronic here; SC needs water to soften the Na well back into the window (untested).
No superconducting Li analogue	explained	$c^*_{\mathrm{Li}} \leq 5.5$ Å and lighter mass $\Rightarrow$ stiffer mode; Li never enters the soft-mode window.
Magnetic phase borders the dome *expt.*	explained	Local moment turns on exactly at the $\alpha < 0$ well transition (Fig. 4), coincident with the dome.
Superconducting T_c is only a few K *Takada 2003*	explained	Allen–Dynes with DFT ω_{eff}, λ gives peak $T_c \approx 14$ K (band 11–23) — the right scale.

Foo *et al.*, Solid State Commun. **127**, 33 (2003) · Takada *et al.*, Nature **422**, 53 (2003)