Density test performed at platform and lower level

Level	Location	Weight (gm)	Volume (ml)	Density (pcf) = W(gm)*62.43/V(ml)
Platform Level	Column B2	63	136	28.91
	Column B1	54	114	29.06
	Beam 5000B1	39	80	30.43
	Column B5	69	146	29.50
	Beam 5014B1	34	74	28.68
	Beam 5015B1	45	88	31.92
Lower Level	Beam 4020B1	41	84	30.47
	Beam 4021B1	69	148	29.10
	Beam 4001B1	41	82	31.22
			Average	30.02

Exceeded the project specifications, 15 pcf

Bond resistance test performed at platform level

Level	Location	Load (p)	Area of Cap (sf)	Strength (psf)
Platform Level	Column B1	4	0.0218	183.48
	Beam 5000B1	11	0.0218	504.58
			Average	344.03

Exceeded the project specifications, 150 psf

Note: Bond resistance was not performed at lower level. Needs reinspection once weather gets better.