

1. SPECIFICATION

1.1 Drawing No. : 26308138

1.2 Mechanical

1.2.1 Composition : Polydimethylsiloxane. Silica

1.2.2 Color in uncured condition : Black

1.2.3 Transparency : Opaque

1.2.4 Viscosity : 14.5 – 25.5 Pa.s

1.2.5 Thixotropy Index : 2.9

1.2.6 Time for 20% Rise in Viscosity at 25°C : > 24 Hours

1.2.7 Durometer Shore A : 72

1.2.8 Specific Gravity (Cured) : 1.2

1.2.9 Unprimed Adhesion - Lap Shear (AI) : 1000 psi

1.2.10 Tensile Strength : 500 psi

1.2.11 Elongation : 25%

1.2.12 Dielectric Strength : 475 volts/mil

1.2.13 Dielectric Constant at 100 Hz : 2.82

1.2.14 Dielectric Constant at 100 kHz : 2.81

1.2.15 Volume Resistivity : 2.10E+15 ohm*cm

1.2.16 Dissipation Factor at 100 Hz : 0.0011

1.2.17 Dissipation Factor at 100 kHz : < 0.0002

1.2.18 Linear CTE (by TMA) : 250 ppm/°C

1.2.19 Impurity (Na+) : 0.5 ppm

1.2.20 Impurity (K+) : 0.75 ppm

1.2.21 Impurity (Cl-) : 2.2 ppm

1.2.22 Typical Curing Time (in air convection oven)

1.2.21.1 at +150 °C : 30 min

1.2.21.2 at +100 °C : 120 min

1.3 Electrical

Not Applicable

1.4 Visual Requirements

- 1.4.1 Dented and leaked packaging will be rejected.
- 1.4.2 Packing with broken seal will be rejected.
- 1.4.3 Wrong part number or expired chemical will be rejected.

					NAME	DATE	DEPARTMENT	
				DRAWN BY	CHUA SH	21.02.2025	ENGINEERING	
				CHECKED BY	YUDHA	21.02.2025	MFGENG	
				DESCRIPTION				PART/ BAU NO
				ADHESIVE DOWSIL ME1070				26308138
A	CMS38911	25.02.25	YUDHA					
REV	ECN NO	DATE	NAME	SUBSTITUTE FOR :		DATED :		PAGE 1 OF 2

- 1.5 Incoming Quality
1.5.1 Refer to Incoming Inspection Criteria.

2. REFERENCE

- 2.1 Manufacturer : DOW
2.2 Product Name : DOWSIL™ ME-1070 Adhesive Black
2.3 Compliant with RoHS directive 2015/863/EU.
2.4 Halogen-free according to IEC 61249-2-21

3. DOCUMENT FROM SUPPLIER

- 3.1 Sample Submission : First Article Report (FAIR), Inspection Report, TDS, SDS, RoHS or Compliant Letter
3.2 Upon Delivery : Delivery Order, CoC, and/or Outgoing Report
3.3 Inspection report will be attached to each lot delivered. Inspection report will include Product name, Lot number, Quantity, Date of Shipment, Appearance and Viscosity

4. PACKING

- 4.1 Container : Cartridge
4.2 Packaging : 10 g per cartridge
4.3 Each packing shall be identified with: Excelitas Bau No., Excelitas Purchase Order, Vendor/Manufacturer Name, Manufacturer Part No., Lot No., Manufacture Date, Expire Date and Quantity.

5. STORAGE / HANDLING / SHELF LIFE

- 5.1 Storage life at -10 to -25°C in unopened original container : 12 months
5.2 Processing time in standard climate +23°C / 50 % r. h. : 48 hours
5.3 The surfaces to be bonded, must be dry as well as free of dust, grease and other contaminations dispensing valves and product-bearing elements must be carefully cleaned directly after adhesive use.

		NAME	DATE	DEPARTMENT	
	DRAWN BY	CHUA SH	21.02.2025	ENGINEERING	
	CHECKED BY	YUDHA	21.02.2025	MFGENG	
	DESCRIPTION				PART/ BAU NO
	ADHESIVE DOWSIL ME1070				26308138
SUBSTITUTE FOR :			DATED :		PAGE 2 OF 2