



AUTOWELD Gr-1

Spec : AWS Sec II-C SFA A5.17/A5.17M
Grade: F7A0-EL8, F7A2-EM12K

Characteristics and Application

AUTOWELD Gr-1 is a high-performance, agglomerated acidic flux designed for demanding fillet welding applications in heavy structural fabrication. It is suitable for Structural steel fabrications Heavy beams, columns, The flux performs exceptionally well in high-deposition fillet welds using single or multi-wire SAW systems under AC or DC polarity, offering consistent quality across horizontal Position.

Features,

- Wide, smooth fillet welds with uniform toe blending and minimal undercut
- Quick and easy slag removal for improved post-weld productivity
- Produces radiographic quality welds free from porosity and slag entrapment

Mechanical Properties of All Weld Metal

SAW WIRE	UTS (Mpa)	Yield strength @0.2% (Mpa)	Elongation %	CVN Impact charpy V-Notch Joules	
				0°C	-20°C
OSCAR SAW-1	550	480	27	38	-
OSCAR SAW-2	580	495	29	-	45

Chemical Composition of All weld metal %

SAW WIRE	C	Mn	Si	S	P	Cu
OSCAR SAW-1	0.05	1.30	0.60	0.024	0.024	0.15
OSCAR SAW-2	0.06	1.55	0.75	0.027	0.020	0.15

Flux Composition

Al2O3	SiO2	MnO	CaF2	MgO	TiO2
45%	15%	5%	10%	5%	20%

Special Features

- Flux consumption as kg Wire / kg Flux – 1 : 1.2
- Basicity Index – 0.8
- Flux Grain Size – 0.5-2.00mm
- Packing – 25kg Poly Lined HDPE Bag

Test results for mechanical properties, deposit or electrode composition and diffusible hydrogen levels were obtained from a weld produced and tested according to prescribed standards, and should not be assumed to be the expected results in a particular application or weld metal. Actual results will vary depending on many factors, including, but not limited to, weld procedure, plate chemistry and temperature, weld metal design and fabrication methods. Users are cautioned to confirm by qualification testing, or other appropriate means, the suitability of any welding consumable and procedure before use in the intended application

OSAR AUTO FLUX
S.F.No 517/1, Veeranampalayam, Kangeyam,
Tiruppur, Tamilnadu – 638701.
Phone: +91-8667753591 | Email: info.oscarautoweld@gmail.com