



OSCAR AUTO FLUX

Manufacturers of Welding consumables

ISO 9001:2008 company

BATCH TEST CERTIFICATE

Oscar Auto Flux S.F.No.517/1, Veerampalayam, Kangeyam,Tiruppur, Tamilnadu - 638701.	Customer Name	Wootz Structures Pvt Ltd		
	Ref. Number	-		
	T.C Number	OAF/QA/021	Date	23-02-2026

Type of flux	Standard	Brand	Grade	Batch.No	Dt. Testing
Agglomerated SAW Flux	AWS A5.17 / SFA 5.17 / EN ISO 14174	AUTO WELD Gr - 3	F7A2 EM12K	3001	18-02-2026

Agglomerated SAW Flux Chemical Composition: (Typical Wt%) As per EN 10204, Type 3.1

Elements	CaO	MgO	Al ₂ O ₃	SiO ₂	TiO ₂	CaF ₂	MnO	Fe ₂ O ₃
Result	10	8	35	15	10	10	10	2

Weldmetal Chemical Properties: (%) As per EN 10204, Type 2.2

Elements	C	Mn	Si	S	P	Cu
Result	0.08	0.98	0.25	0.02	0.02	0.15

Weldmetal Mechanical Properties: (Typical Value) As per EN 10204, Type 2.2

Test	Condition	Tensile Strength (Mpa)	Yield Strength (Mpa)	Elongation %	Charpy V Notch Impact Test		Radiography	Moisture
					CVN Avg	°C		
Requirement	AW	490 - 660	>400	>22	>27	-20	Passed	0.01
Result	AW	525	430	27	43	-20		

Grain Size Distribution: (%) As per EN 10204, Type 3.1

Grain Size (mm)	2.0 - 1.7mm	1.7 - 1.0mm	1.0 - 0.8mm	0.8 - 0.6mm	0.6 - 0.4mm	< 0.4mm
(%) of Retention	0	32	45	15	2	1

As per EN 10204, Type 3.1

Additional Information / Informations Complementaires:

Basicity Index	0.9
----------------	-----

Remark:

The above the result are typical and provided for reference only.

Tests conducted using submerged arc welding process in accordance with ASME Sec-II Part-C Edition 2023.

The certificate is issue based on non-specific and testing as per EN 10204 Type 2.2 & 3.1.

No specific lot testing or traceability is provided under this certificate type.

Authorized signatory

Quality Manager, OSCAR AUTO FLUX.

S.F.No 517/1, Veeranampalayam, Kangeyam, Tiruppur, Tamilnadu – 638701.

Phone: +91-8667753591 | Email: info.oscarautoweld@gmail.com

Registered with MSME | GSTIN: 33CQZPR8943L1ZM

All correspondence should be addressed to the registered office.

S