Mumbai : H-123, Lokmanya Nagar, Mahim, Mumbai
Pune : 303, Spandan Residency, Popular Nagar, Pune
Aurangabad : C-150, MIDC Waluj, Aurangabad - 431 136. 0240-2554065
Kolhapur : 23, Vidya Colony, Post Market Yard, Kolhapur.
Satara : 3, Tribhuvan Apartment, Yadogopal Peth, Satara
E-mail : mattestlab@gmail.com
Cell : +91 09823012371

MATTEST

Test Report

Customer's Name	Nihva Technologies Pvt Ltd	(F/7.8/1 , Rev 0)
		Report No. P1961
		Date: 17-11-2021
Customer's Ref.	TR Dated 16-11-2021	Condition of Sample : CUT PIECE
Nature of Sample	TEST PIECE	Sample Received on : 17-11-2021
Specification	**EN AW-6060**	Date of Completion : 17-11-2021
Sample Drawn By	Customer	
Deviation if Any	Nil	Enclosure : NIL
Test :	Hardness, CHEMICAL ANALYSIS	
Sample Identification	ALUMINIUM BOTTOM	

I. Chemical

1.

CHEMICAL ANALYSIS

Test Method : ASTM E1251:2017

	Result	Reqd.
% Silicon (Si)	0.488	0.30-0.60
% Iron (Fe)	0.300	0.10-0.30
% Copper (Cu)	0.059	0.10 max.
% Manganese (Mn)	0.089	0.10 max.
% Magnesium (Mg)	0.373	0.35-0.60
% Chromium (Cr)	0.038	0.05 max.
% Zinc (Zn)	0.150	0.15 max.
% Titanium (Ti)	0.023	0.10 max.
% Aluminium (Al)	Remainder	Remainder

Remarks The material conforms to EN AW-6060 with respect to test/s carried out.

II. Mechanical

2.

Hardness Test

Test Method : MT 02 *

	Result
Hardness, 15T Scale (Rockwel Superficial Hardness)	62
Approx. Conversion to Hardness, HRB (Refer Fine Chart)	40

----------End of Report----------

For Mattest Laboratory

AUTHORISED SIGNATORY

Note :1) This report refers only to the particular item(s) submitted for testing.
2) This report shall not be reproduced,except in full, unless written permission for the publication of an approved abstract has been obtain from the CEO, Mattest Laboratory.
3) The customers are advised to take into account the CURRENTLY PREVAILING ACCURACY AND UNCERTAINTY VALUES while

Mumbai : H-123, Lokmanya Nagar, Mahim, Mumbai.
Pune : 303, Spandan Residency, Popular Nagar, Pune.
Aurangabad : G-150, MIDC Waluj, Aurangabad - 431 136. 0240-2554065
Kolhapur : 23, Vidya Colony, Post Market Yard, Kolhapur.
Satara : 3, Tribhuvan Apartment, Yadogopal Peth, Satara.
E-mail : mattestlab@gmail.com
Cell : +91 09823012371

MATTEST

Test Report

Customer's Name Nihva Technologies Pvt Ltd

(F/7.8/1 , Rev 0)
Report No. P1962
Date: 17-11-2021

Customer's Ref. TR Dated 16-11-2021
Nature of Sample TEST PIECE
Specification **EN AW-6060**
Sample Drawn By Customer
Deviation if Any Nil

Condition of Sample : CUT PIECE
Sample Received on : 17-11-2021
Date of Completion : 17-11-2021

Enclosure : NIL

Test : Hardness, CHEMICAL ANALYSIS

Sample Identification ALUMINIUM CONNECTOR

I. Chemical

1.

CHEMICAL ANALYSIS
Test Method : ASTM E1251:2017

	Result	Reqd.
% Silicon (Si)	0.463	0.30-0.60
% Iron (Fe)	0.300	0.10-0.30
% Copper (Cu)	0.055	0.10 max.
% Manganese (Mn)	0.089	0.10 max.
% Magnesium (Mg)	0.365	0.35-0.60
% Chromium (Cr)	0.037	0.05 max.
% Zinc (Zn)	0.147	0.15 max.
% Titanium (Ti)	0.023	0.10 max.
% Aluminium (Al)	Remainder	Remainder

Remarks The material conforms to EN AW-6060 with respect to test/s carried out.

II. Mechanical

2.

Hardness Test
Test Method : MT 02 *

	Result
Hardness, BHN	72

----------End of Report----------

For Mattest Laboratory

AUTHORISED SIGNATORY

Note :1) This report refers only to the perticular item(s) submitted for testing.
2) This report shall not be reproduced,except in full, unless written permission for the publication of an approved abstract has been obtain from the CEO, Mattest Laboratory.
3) The customers are advised to take into account the CURRENTLY PREVAILING ACCURACY AND UNCERTAINTY VALUES while making decisions about acceptance or rejection of their material based on grade confirmation statement. The values are readily available with Quality Manager.

Mumbai : H-123, Lokmanya Nagar, Mahim, Mumbai
Pune : 303, Spandan Residency, Popular Nagar, Pune
Aurangabad : C-150, MIDC Waluj, Aurangabad - 431 136. 0240-2554065
Kolhapur : 23, Vidya Colony, Post Market Yard, Kolhapur
Satara : 3, Tribhuvan Apartment, Yadogopal Peth, Satara
E-mail : mattestlab@gmail.com
Cell : +91 09823012371

MATTEST

Test Report

Customer's Name	Nihva Technologies Pvt Ltd	(F/7.8/1 , Rev 0)
		Report No. P1964
		Date: 17-11-2021
Customer's Ref.	TR Dated 16-11-2021	Condition of Sample : CUT PIECE
Nature of Sample	TEST PIECE	Sample Received on : 17-11-2021
Specification	**EN AW-6060**	Date of Completion : 17-11-2021
Sample Drawn By	Customer	
Deviation if Any	Nil	Enclosure : NIL
Test :	Hardness, CHEMICAL ANALYSIS	
Sample Identification	ALUMINIUM GUIDE	

I. Chemical

1.

CHEMICAL ANALYSIS

Test Method : ASTM E1251:2017

	Result	Reqd.
% Silicon (Si)	0.412	0.30-0.60
% Iron (Fe)	0.115	0.10-0.30
% Copper (Cu)	Nil	0.10 max.
% Manganese (Mn)	Nil	0.10 max.
% Magnesium (Mg)	0.477	0.35-0.60
% Chromium (Cr)	Ni	0.05 max.
% Zinc (Zn)	0.023	0.15 max.
% Titanium (Ti)	0.018	0.10 max.
% Aluminium (Al)	Remainder	Remainder

Remarks The material conforms to EN AW-6060 with respect to test/s carried out.

II. Mechanical

2.

Hardness Test

Test Method : MT 02 *

	Result
Hardness, BHN	72

----------End of Report----------

For Mattest Laboratory

AUTHORISED SIGNATORY

Note :1) This report refers only to the particular item(s) submitted for testing.
2) This report shall not be reproduced,except in full, unless written permission for the publication of an approved abstract has been obtain from the CEO, Mattest Laboratory.
3) The customers are advised to take into account the CURRENTLY PREVAILING ACCURACY AND UNCERTAINTY VALUES while making decisions about acceptance or rejection of their material based on grade confirmation statement. The values are readily available with Quality Manager.

ON APPROVED LIST OF GOVERNMENT DEPARTMENTS