SYNTHETIC ENAMEL PAINT

PRODUCT DATA SHEET

PRODUCT DESCRIPTION

Single pack, air drying, glossy alkyd finishing paint

FEATURES AND RECOMMENDED USE

- Glossy enamel suitable for interior and exterior use
- Suitable under industrial & coastal atmospheric conditions
- Easy application by brush with excellent flow
- Good weather resistance
- Good colour retention
- Conforms to IS 2932: 2003

TECHNICAL DATA

Colour	As per available range
Gloss	Glossy/Semi Glossy
Volume Solids	38%
Recommended DFT/Coat	20-25 microns
Theoretical Coverage	12 to 15 Sqm Per Ltr /Per Coat
Drying Time at 30°C	Surface Dry: 4 hours Hard Dry: 12 hours
Over coating interval at 30°C	Minimum: 12 hours Maximum: Unlimited, provided surface is dry and clean from all contamination

DIRECTIONS FOR USE

Surface Preparation

- Ensure removal of dirt, dust, oil and all other contaminants that could interfere with adhesion of the coating.
- Suitable alkyd / epoxy primer or intermediate coat, dry and free from any contamination.
- Oil and grease should be removed as per SSPC-SP1 solvent cleaning.
- In case of aged alkyd or epoxy coating, the surface should be sufficiently roughened if necessary
- The surface should be thoroughly dry and free from moisture before painting

Application Conditions

- Surface temperature must be at least 3°C above dew point but not above 50°C
- Do not paint at temperatures below 10°C or at relative humidity over 85%
- Under cold and humid conditions, the paint would require longer drying time
- Good ventilation is required in confined areas to ensure proper curing

Trident Engineering
2339 Nani Makeriwad, Kadia Kui, Relief Road,
Ahmedabad - 380001 | www.tridentin.com

MIXING

If settling is observed in the drum, loosen the settled material with the help of hand stirrer followed by power driven stirrer for quick homogenous mixing

- Thinner should be added after mixing. Addition of excessive thinner will lead to reduced sag resistance.

APPLICATION

Brush / Roller	Recommended Thinner: Trident Thinner Volume of Thinner: 0-5%
Air Spray	Recommended Thinner: Trident Thinner Volume of Thinner: 10-20% Nozzle Orifice: 1.5 – 3.0 mm Nozzle Pressure: 0.3 - 0.4 MPa (approx. 3-4 atm, 43-57 p.s.i)
Airless Spray	Recommended Thinner: Trident Thinner Volume of Thinner: 0-5% Nozzle Orifice: 0.28 mm Nozzle Pressure: 12 MPa (=approx. 120 atm, 1700 p.s.i)

STORAGE & PACKING

Storage: A minimum shelf life of 12 months when stored in a cool, dry and covered place

Packing: 20 litres

SAFETY INFORMATION

- As a general safety measure, inhalation if paint mist and contact of liquid paint with skin & eyes should be avoided
- Forced ventilation should be provided when applying paint in confined spaces or stagnant air
- Even when ventilation is provided, respiratory, skin and eye protection are always recommended when spraying paint
- Please refer our Material Safety Data sheet prior using the product

DISCLAIMER

The information provided on this data sheet is not intended to be complete and is provided as general advice only. It is the responsibility of the user to ensure that the product is suitable for the purpose for which he wishes to use it. As we have no control over the treatment of the product, the standard of surface preparation of the substrate, or other factors affecting the use of this product, we are not responsible for its performance nor would we accept any liability whatsoever or howsoever arising from the use of this product unless specifically agreed to in writing by us. The information contained in this data sheet may be modified by us from time to time, and without notice, in the light of our experience and continuous product development.

Trident Engineering
2339 Nani Makeriwad, Kadia Kui, Relief Road,
Ahmedabad - 380001 | www.tridentin.com