TECH BRIEF

Build On.

Flat Sheet Polycarbonate & International Building Code Compliance

Flat Sheet Polycarbonate & International Building Code Compliance

Overview:

The provisions of IBC, Chapter 26, Section 2606, Light Transmitting Plastics govern the quality and methods of application of light-transmitting plastics for use as light transmitting materials in buildings and structures.

Test Standard Definition:

ASTM D1929 – Self Ignition Temperature
Complying plastic materials must have a self-ignition temperature of > 650°F (343°C).

ASTM D635 – Horizontal Burn Rate
Complying plastic materials shall achieve one of two classifications: CC1 or CC2.
CC1 = Plastic materials having a burning extent of 1" or less.
CC2 = Plastic materials having a burning rate of 2.5 inches per minute or less.

ASTM D2843 – Smoke Density
Complying plastic materials must achieve a smoke density <75 when tested in the thickness intended for use.

Palsun Basic, Palsun UV, Palsun FR, Palsun CS, Palgard achieve the following results:

Test Standard	Required Test Value	Test Value Achieved
ASTM D1929 - Self Ignition	> 650F	>875F
ASTM D635 - Horizontal Burn Rate	CC1 or CC2	CC1
ASTM D2843 - Smoke Density	< 75	<75

Palsun Basic, Palsun UV and Palgard are also listed under International Code Council (ICC) Evaluation Report ESR-1893 as approved light transmitting plastics.

The information presented above is to be used for informational purposes only and is accurate to the best of our knowledge. Please consult the prevailing building code to determine compliance.

Palram Americas, Inc.
ISO 9001:2015

Customer Service
9735 Commerce Cir.,
Kutztown, PA 19530 Phone:
800-999-9459,
+1-610-285-9918
Fax: +1-610-285-9928
E-Mail: sales.usa@palram.com

Technical Service
Phone: 800-999-9459 Ext. 292
Fax: +1-610-285-9928

palram.com/us

Inasmuch as Palram Americas has no control over the use (and/or installation method) to which others may put this material, it does not guarantee that the same results as those described herein will be obtained. Each user of the material should make their own test to determine the suitability of the material for their own particular use. In the event of a warranty claim for product failure, Palram Americas reserves the right to inspect any or all of the sheets involved and the installation site itself while the sheets are still in their original position and have not been removed or moved or altered in any way.
© 2021 Palram Americas