AMENDMENT NO. 2 AUGUST 2008
TO
IS 277 : 2003 GALVANIZED STEEL SHEETS (PLAIN AND CORRUGATED) — SPECIFICATION

(Sixth Revision)

[*Page* 1, *clause* 6 (*see also Amendment No.* 1)] — Insert the following grades in the existing table:

Sl No.	Type	Designation	Grade Reference of Base Metal IS 1079/IS 513
(1)	(2)	(3)	(4)
v)	Ordinary	GP	Grade O
vi)	Ordinary-Hard	GPH	Grade O
vii)	Lock Forming	GPL	Grade D

(*Page* 1, *clause* 5.2) — Insert the following new clause after 5.2:

'5.3 Passivation shall be carried out on the surface, if agreed to between the purchaser and the manufacturer.'

(*Page* 2, *clause* 7.4) — Insert the following new clause after 7.4:

'7.5 If agreed to between the purchaser and the manufacturer, the grade of coatings 100 and 80 may be used for non-critical applications other than roofing. The mass of coating in such cases shall be as follows:

Grade of Coating	Minimum Average Coating Triple Spot Test g/m^2	Minimum Coating Single Spot Test g/m^2
(1)	(2)	(3)
100	100	90
80	80	75
NOTE – For the above grade of coating, the mandrel diameter for bend test for adhesion of zinc coating shall be subject to mutual agreement between the purchaser and the manufacturer.		

Not for sale