GLORIA ALLUMINIUM INDIA PVT LTD

Plot No. B-18, Chakan Industrial Area,Phase II,MIDC,Vasuli,Khed,Pune-410501

TEST REPORT

CUSTOMER NAME :- NIHVA TECHNOLOGIES

Test Report No-GLO/648F	
Date of Testing- 31-01-2023	
Date of Reporting-31-01-2023	
Die no:- GNT 002	
Invoice No:-	1188
Date:-	10-02-2023

Sample Identification -	Alluminium Sections
Matrix	Al_Low Alloys
Test Required -	Chemical Composition By Optical Emission Spectrometer
Test Method -	As per IS 733-1983
Special Requirements -	Actual Hardness:-67 BHN
Material Specifications -	Alloy 6063-T6

RESULT OF ANALYSIS

Sr No	Elements	Burn 1	Burn 2	Specifications		Observed (Mean)
				Min	Max	
1	Si (%)	0.4956	0.4991	0.20	0.60	0.4974
2	Fe (%)	0.3249	0.3272	-	0.35	0.3261
3	Cu (%)	0.0325	0.0327	-	0.10	0.0326
4	Mg (%)	0.5051	0.5126	0.45	0.90	0.5089
5	Mn (%)	0.0327	0.0324	-	0.10	0.0326
6	Ti (%)	0.0133	0.0137	-	0.10	0.0135
7	Zn (%)	0.0139	0.0084	-	0.10	0.0112
8	Ni (%)	0.0000	0.0000	-	-	0.0000
9	Pb (%)	0.0000	0.0000	-	-	0.0000
10	Sn (%)	0.0276	0.0200	-	-	0.0238
11	Cr (%)	0.0078	0.0072	-	0.10	0.0075
12	Be (%)	0.0000	0.0000	-	-	0.0000
13	Sr (%)	0.0000	0.0000	-	-	0.0000
14	Zr (%)	0.0015	0.0000	-	-	0.0008
15	Ca (%)	0.0056	0.0057	-	-	0.0057
16	V (%)	0.0117	0.0118	-	-	0.0118
17	Al (%)	98.5276	98.5290	-	-	98.5283

NOTE -

1) **All Elements are Reported in Percentage Except where Unit Specified.**
2) **Sample will be disposed after 30 days from the date of material testing.**

GLORIA ALLUMINIUM INDIA PVT. LTD.

Authorized Sign

GLORIA ALLUMINIUM INDIA PVT LTD

Plot No. B-18, Chakan Industrial Area,Phase II,MIDC,Vasuli,Khed,Pune-410501

TEST REPORT

CUSTOMER NAME :- NIHVA TECHNOLOGIES

Test Report No-GLO/648F	
Date of Testing- 31-01-2023	
Date of Reporting-31-01-2023	
Die no:- GNT 006	
Invoice No:-	1188
Date:-	10-02-2023

Sample Identification -	Alluminium Sections
Matrix	Al_Low Alloys
Test Required -	Chemical Composition By Optical Emission Spectrometer
Test Method -	As per IS 733-1983
Special Requirements -	Actual Hardness:-67 BHN
Material Specifications -	Alloy 6063-T4

RESULT OF ANALYSIS

Sr No	Elements	Burn 1	Burn 2	Specifications		Observed (Mean)
				Min	Max	
1	Si (%)	0.4956	0.4991	0.20	0.60	0.4974
2	Fe (%)	0.3249	0.3272	-	0.35	0.3261
3	Cu (%)	0.0325	0.0327	-	0.10	0.0326
4	Mg (%)	0.5051	0.5126	0.45	0.90	0.5089
5	Mn (%)	0.0327	0.0324	-	0.10	0.0326
6	Ti (%)	0.0133	0.0137	-	0.10	0.0135
7	Zn (%)	0.0139	0.0084	-	0.10	0.0112
8	Ni (%)	0.0000	0.0000	-	-	0.0000
9	Pb (%)	0.0000	0.0000	-	-	0.0000
10	Sn (%)	0.0276	0.0200	-	-	0.0238
11	Cr (%)	0.0078	0.0072	-	0.10	0.0075
12	Be (%)	0.0000	0.0000	-	-	0.0000
13	Sr (%)	0.0000	0.0000	-	-	0.0000
14	Zr (%)	0.0015	0.0000	-	-	0.0008
15	Ca (%)	0.0056	0.0057	-	-	0.0057
16	V (%)	0.0117	0.0118	-	-	0.0118
17	Al (%)	98.5276	98.5290	-	-	98.5283

NOTE -

1) **All Elements are Reported in Percentage Except where Unit Specified.**
2) **Sample will be disposed after 30 days from the date of material testing.**

GLORIA ALLUMINIUM INDIA PVT. LTD.

Authorized Sign

GLORIA ALLUMINIUM INDIA PVT LTD

Plot No. B-18, Chakan Industrial Area,Phase II,MIDC,Vasuli,Khed,Pune-410501

TEST REPORT

CUSTOMER NAME :- NIHVA TECHNOLOGIES

Test Report No-GLO/630F
Date of Testing- 31-01-2023
Date of Reporting-31-01-2023
Die no:- GNT 007

Invoice No:- 1188
Date:- 10-02-2023

Sample Identification -	Alluminium Sections
Matrix	Al_Low Alloys
Test Required -	Chemical Composition By Optical Emission Spectrometer
Test Method -	As per IS 733-1983
Special Requirements -	Actual Hardness:-67 BHN
Material Specifications -	Alloy 6063-T6

RESULT OF ANALYSIS

Sr No	Elements	Burn 1	Burn 2	Specifications		Observed (Mean)
				Min	Max	
1	Si (%)	0.4956	0.4991	0.20	0.60	0.4974
2	Fe (%)	0.3249	0.3272	-	0.35	0.3261
3	Cu (%)	0.0325	0.0327	-	0.10	0.0326
4	Mg (%)	0.5051	0.5126	0.45	0.90	0.5089
5	Mn (%)	0.0327	0.0324	-	0.10	0.0326
6	Ti (%)	0.0133	0.0137	-	0.10	0.0135
7	Zn (%)	0.0139	0.0084	-	0.10	0.0112
8	Ni (%)	0.0000	0.0000	-	-	0.0000
9	Pb (%)	0.0000	0.0000	-	-	0.0000
10	Sn (%)	0.0276	0.0200	-	-	0.0238
11	Cr (%)	0.0078	0.0072	-	0.10	0.0075
12	Be (%)	0.0000	0.0000	-	-	0.0000
13	Sr (%)	0.0000	0.0000	-	-	0.0000
14	Zr (%)	0.0015	0.0000	-	-	0.0008
15	Ca (%)	0.0056	0.0057	-	-	0.0057
16	V (%)	0.0117	0.0118	-	-	0.0118
17	Al (%)	98.5276	98.5290	-	-	98.5283

NOTE -

1) **All Elements are Reported in Percentage Except where Unit Specified.**
2) **Sample will be disposed after 30 days from the date of material testing.**

GLORIA ALLUMINIUM INDIA PVT. LTD. PUNE

Authorized Sign

Gloria Alluminium India Pvt Ltd

Plot no-B/18,Chakan Industrial Area,Phase II,MIDC,Vasuli Khed,Pune

Alloy:- 6082 - T6

PART NO:- GNT-007

CUSTOMER NAME:- NRHVA

Operation Disc.:-Extrusion

Pre-Dispatch Inspetion Report

Rev:-

DATE:- 31/01/2023

CASTING NO: 630

SR.NO.	PARAMETER	SPECIFICATION	INSPECTION METHOD	INPROCESS INSPECTION					REMARK
				1	2	3	4	5	
1	Dim	99.0 ± 1.00	Vc	99.17	99.20	99.22	99.19	99.16	OK
2	—11—	63.3 ± 0.20	VC	63.22	63.16	63.19	63.25	63.24	OK
3	—11—	46.5 ± 0.20	VC	46.61	46.60	46.70	46.65	46.68	OK
4		21.00	"	20.92	20.94	20.91	20.93	20.95	OK
5	THK	2.5 ± 0.20	"	2.23	2.31	2.29	2.28	2.25	OK
6	"	2.6	"	2.35	2.25	2.30	2.34	2.37	OK

Note: We are consider tolerance ±0.20mm and all dimensions are in mm.

Accepted/Rejected

Inspected By: Alkesh singh

Verified By: Ajeet singh

GLORIA ALLUMINIUM INDIA PVT. LTD. PUNE