UltraLite®UV2 3.0 mm Solid Polycarbonate Sheet Clear

UltraLite® UV2, 3.0 mm clear sheets are made from clear-transparent Makrolon polycarbonate Resin with UV protection on both sides. They are the perfect choice for a long service life owing to their good weathering resistance. These attributes are backed up by our 10 year limited manufacturing guarantee on weathering resistance and a 10-year guarantee on retaining their mechanical properties.

Color:- Clear

Thickness: 3.00 mm

UV absorbant layer thickness:- 50µ

Light Transmission:- 88±3%

Available Sizes are: UltraLite® UV2 According to thickness available sizes are as following.

1220X2440 MM , 2050X 3050 MM
1220X30500MM,2050X30500 MM

(Other sizes are available on request and also according to transportation facility.)

Application: UltraLite® UV2 is ideal for outdoor and indoor applications:

- covered walk ways and bus shelters, signboards
- barrel vaults and skylights

Product data sheet 2021

UltraLite® UV2 solid sheets
3.0 mm SOLID POLYCARBONATE SHEET CLEAR
Silent, Safe, Sustainable
PC Sheets – Make in India

Advantages:


Extreme Impact strength
Virtually unbreakable
Good fire rating
Thermoformable
Good Light transmission
ISI approved
Both side UV Coated

Recyclable



Technical data

Property	Test condition	Typical Values	Unit	Test Method
Physical				
Density		1.2	g/cm3	ASTMD792
Moisture absorption	23°C/50%RH	0.15	%	ASTMD570
Refractive Index		1.58	-	ASTMD542
Mechanical				
Tensile stress at yield		>60	MPa	ASTMD638
Tensile Strength		>60	MPa	ASTMD638
Elongation at break		110	%	ASTMD638
Elastic Modulus		2400	MPa	ASTMD638
Limiting Flexural stress		93.1	MPa	ASTMD790
Impact Strength Izod	Un notched @3.17	NB	J/cm	ASTMD256
Impact Strength Izod	Notched @3.17	8.54	J/cm	ASTMD256
Rockwell Hardness		118	R	ASTMD785
Thermal				
Thermal conductivity		0.2	W/mK	ASTMDC177
Coeff, of liner thermal expansion		0.065	Mm/m °C	DIN 53752-A
HDT under load	1.80 Mpa	132	°C	ASTMD648
	0.45 Mpa	142	°C	ASTMD648
Electrical				
At 3.0 mm thickness Dielectric Strength		15	kV/mm	ASTMD149
Volume resistivity		10^{16}	Ohm ·cm	ASTMD257
Surface resistivity		10^{14}	Ohm	IEC 60093
Dielectric constant	At10Hz	3		ASTMD150
	At60Hz	3.17		ASTMD150
Dissipation factor	At60Hz	0.0009		ASTMD150
At 3.0 mm thickness Fire rating≤	Based on resin test	V2		UL 94



*The mechanical properties were measured on sheets of 4mm or 3mm thickness.

Product Liability Clause: This information and our technical advice whether verbal, in writing or by way of trials are given in good faith but without warranty, and this also applies where proprietary rights of third parties are involved. Our advice does not release you from the obligation to verify the information currently provided especially that contained in our safety data and technical information sheets–and to test products as to their suitability for the intended processes and uses. The application, use and process in go for products and the products manufactured by you on the basis of our technical advice are beyond our control and, therefore, entirely your own responsibility. Our products are sold in accordance with the current version of our General Conditions of Sale and Delivery