FERROCOAT POWDERS	TEST REPORT	Doc. No.:QA/F/13 Issue no.: 02 issue Date: 03 10 2023

PRODUCT CODE :- 6850
PRODUCT NAME :- RAL 5010 (Gentian blue)
BATCH NO./LOT NO. :- B1000/23-24
TYPE OF PRODUCT : HYBRID

DATE : 10/01/2024
PAGE : 01 of 01

S.No.	DESCRIPTION	SPECIFICATION	OBSERVATION	RESULT
1	Substrate (mm, crca)	0.6	0.6	OK
2	Application by Electrostatic Spray Gun	50-90KV	60 80KV	OK
3	Baking Schedule (°C/Minute)	200/ 10-12	200/10	OK
4	Shade/ Colour (Visual)	Close Match to Standard	Close Match	OK
5	Coating Thickness (Microns)	70-90 Microns	75 85	OK
6	Surface Finish	Smooth	Smooth	OK
7	Gloss (60° Head) ASTM D-523	47+/-2	45 46	OK
8	Bend Test (5mm Rod Dia) Cylindrical Mandrel, ASTM D-522	No Cracks In The Coating Film	No Cracks Observed	OK
9	Impact (kg-cm), ASTM D-2794			
	Direct	80(Minimum)	120(Passes)	OK
	Indirect	80(Minimum)	120(Passes)	OK
10	Erichsen Cupping (mm), ENISO-20482	>6	7(Passes)	OK
11	Adhesion, ASTM D-3359	5B or GT-0	GT 0	OK
12	Scratch Hardness, Kgs (1S-101)	>2.5	3Kgs.	OK
13	Specific Gravity	1.6+/-0.2	1.65	OK
14	ROHS Status	Compliance	Compliant	OK
15	Humidity Test, 95% Rh (Approx.) Temp 38+/- 3°C for 1000 Hrs. ASTM D-2247	No sign of film Deterioration & Corrosion Below The Coating Film	It will be Pass(Based on Resin chemistry)	OK
16	Salt Spray Test at 35+/- 3°C for 1000 Hrs, 5% Sodium Chloride Solution ASTM B-117	No Blister Formation, Rust Creepage From The Scratch, 5 mm Maximum	It will be Pass(Based on Resin chemistry)	OK
17	(A) Particle Size Distribution % By Volume), Malvern -2000			
	_Under 10 Microns	<11%		
	_Under 60 Microns	82+/ 5%		
	B) d(0.5) Micron	36+/-2		
	*OR Powder Passing Through Sieve (% by Weight)			
	37 Micron	45-60%	48.26%	OK
	63 Micron	94+/ 5%	93.42%	OK
18	UV resistance ASTM G-154	500 hours		OK

REMARKS:

Note:- Above results are based on test conducted in our laboratory under controlled condition.

Sign. & Date	10/01/24 TESTED BY	10-01-24 VERIFIED BY

QUALITY CONTROL QC QUALITY CONTROL