TILARA®
YOUR PARTNER FOR GROWTH, GAIN & GOODWILL

TEST REPORT

We Certify that the Material described belowfully conforms to the requirement of IS 14443:1997. Properties of the product as tested in accordance with scheme of Inspection and testing contained in the BIS Certification marks Licence No.: CM/L-7600154113 are as indicated below against each order.

Date of Issue:-01.02.2024

Date of performance of testing:-04-01-2024

Sampling details: Random Sampling

Lot No:-Y6/A/240104

Sample Details: Compact Polycarbonate Clear Sheet-3.00mm
Test condition: 27 °C / 63%RH

TEST RESULT

Sample	Test property	Unit	Test method	Standard Value	Test Value
Sample As Above	Operating Temperature	°C	-	(-20°C to 140°C)	120°C
	Density	gm/cm3	ISO 1183	1.2	1.2
	Uv Layer Measurement On Both Sides	µm	Microscope	40-50	49.65-50.87
	Light Transmittance	%	ASTM D 1003	80-90%	88.50%
	Falling Dart Drop Impact	Joule	ASTM D 1709	150-155Joule	155J
	Flammability test	-	ASTM E119	UL94	V2
	Taber Abrasion Resistance	%	ASTM D1044-19 ASTM D1003	500 Cycles Rotatums, Reduction in	3%
	Izod Impact Strength(notched)	kg·cm²	ASTM D256	1.84 mm notch	98.54

IS 14443
CM/L-7600154113

ISO®

Authorized Signatory