Polycarbonate sheet - Technical Specifications

GENERAL			
General Properties	Method	Units	Value
Density	ISO 1183	g/cm3	1.2
Light Transmission (Depending on thickness)	ASTM D 1003	%	81-90
Reflective index	ISO 489		1585
MECHANICAL			
General Properties	Method	Units	Value
Tensile Strength at yield	ISO 527-2	MPa	60
Tensile Modulus	ISO 527-2	MPa	2300
Elongation at break	ISO 527-2	%	>100
Elongation at yield		%	6
Flexural Modulus	ISO 178	MPa	2330
Charpy Un-notched	ISO 179	KJ/m2	Not Break
Izod Impact notched	ISO 180a	KJ/m2	> 65
THERMAL			
General Properties	Method	Units	Value
Temp of deflection (HTD) Under load of 1.8 MPa	ISO 75-1	°C	130
Vicat softening temp (50 °C/h 50N)	ISO 306	°C	144
Thermal conductivity	DIN52612	W/m x°C	0.2
Coefficient of linear thermal expansion 0-50°C	ISO 11359	mm/(mx1°C)	0.07
GWFI (Glow-wire Flammability index)	IEC60695-2	°C	900
ELECTRICAL			
General Properties	Method	Units	Value
Volume Resistivity	IES 60093	Ω x cm	3 x 1014
Surface Resistivity, dry	IEC 60093	Ω	6 x 1015
Dissipation Factor 1Mhz	IEC60250		0.009
Dissipation Factor 100Hz	IEC60250		0.0006