

HBS formation as a second-order phase transition

A Landau functional for SCIANTIX

E. Cappellari

September 10, 2026

SCIANTIX status

The model

Results

Model applied to SCIANTIX

Outlook: from a local functional to a phase field

SCIANTIX status

SCIANTIX had three formation models for the restructured volume fraction

option	form	driven by
1	KJMA, Barani (2020) ¹	effective burnup
2	KJMA + $bu_{inc} = 15$, Biswas and Aagesen (2025) ²	effective burnup
3	KJMA on ρ_d , Veshchunov ³ + Zullo (2026)	local burnup

All three are **transformation kinetics**: a sigmoid fitted in burnup. None of them produces the **mean misorientation** Θ of the subgrains, or the **subgrain radius** r_n .

¹ Barani et al., *J. Nucl. Mater.* 539 (2020) 152296.

² Biswas and Aagesen, *Comput. Mater. Sci.* 258 (2025) 114052, Eq. 45.

³ Veshchunov and Shestak, *J. Nucl. Mater.* 384 (2009) 12–18.

The data this model is built on

EBSD — Zacharie-Aubrun *et al.* (2022), Onofri *et al.* (2025). 42 radial positions on 7 rods, with TRANSURANUS local conditions.

quantity	N	what it is
mean misorientation Θ	41	$[A_{\text{Mis}}(f_1 - f_{10}) + 10f_{10}]/100$
restructured fraction X	27	f_{10} , area fraction above 10°
subgrain radius r_n	14	ECD50 % /2

1° is the lower bin edge of the dataset.

What KJMA is, and what it assumes

Nuclei appear *at random* in the untransformed material and grow *isotropically*; count the transformed volume as if the growing regions could overlap freely, the **extended volume** V_e , and the overlap correction is statistical:

$$dX = (1 - X) \frac{dV_e}{V} \implies X = 1 - \exp(-K t^n)$$

What you get

K and n , and a sigmoid. n carries the dimensionality of growth and the nucleation regime.

What it assumes

Randomly placed nuclei, a growth law independent of where you are in the transformation, and a *time dependence*.

The time dependence in the KJMA model

- 1 **Effective burnup**, $n = 3.54$, $K = 2.77 \times 10^{-7}$, fitted on restructured-fraction data.
- 2 Same, with an **incubation burnup** $bu_{inc} = 15 \text{ MWd/kgHM}$ below which nothing happens. Biswas & Aagesen get it from a balance between the energy stored in dislocations and the energy of forming a subgrain used to shift the origin of an empirical curve rather than to build the curve.
- 3 KJMA not on burnup but on the **dislocation density** $\rho_d(bu, T)$, with a threshold $\rho_{crit} = 6 \times 10^{14} \text{ m}^{-2}$. The first to make the driver a **microstructural state variable** and the only one that feels temperature.

What none of them can do

They are calibrated on X alone. There is no misorientation angle neither subgrain size.

Why a phase transition could be the right shape for this problem

The HBS forms *continuously*

Not by nucleating new grains, but by low-angle boundaries absorbing dislocations until their misorientation drifts through the 10° HAGB threshold. In the metallurgical literature this is *continuous* dynamic recrystallization, and it is a well-posed alternative to the nucleation-and-growth picture KJMA describes.⁵

A continuous transformation has an order parameter

If a single continuous quantity distinguishes the two states, Landau's argument applies: expand the free energy in it, and keep only the terms symmetry allows.⁶

$$F(\eta) = C_0 + C_2\eta^2 + C_4\eta^4$$

Odd powers are forbidden here since the energy of a boundary cannot depend on the *sign* of the misorientation across it.

C_2 changing sign produces the transition between a null order parameter and a non-zero one, i.e. the development of misorientation.

⁵Gourdet & Montheillet, *Acta Mater.* 51 (2003) 2685; Humphreys & Hatherly (2017), chs. 6 and 10.

⁶Landau (1937); Landau & Lifshitz, *Statistical Physics I*, §143.

Landau against KJMA, side by side

	KJMA (options 1–3)	Landau (option 4)
what is solved	a <i>kinetic</i> law along a path	the <i>equilibrium</i> of a state
driver	burnup or ρ threshold	$\rho(bu)$ through C_2
free parameters	K , n fitted on X	β , k , ρ_c fitted on Θ , r_n
predicts X	by construction	yes
predicts Θ , r_n	no	yes
reversible?	no, monotone by construction	yes — see below

The price of using an equilibrium theory

A drop in ρ_{tot} would un-restructure the fuel. Restructuring is irreversible, so the implementation carries a **monotonic lock** on Θ . However, this is easy if one considers the dislocation density generated by irradiation, and eventually includes the annealing phenomena within the evolution of the Landau free energy.

The model

HBS as a second-order phase transition

Order parameter

$$\eta = \frac{\theta}{\theta_{\max}}, \quad \theta_{\max} \equiv \theta_{\text{HAGB}} = 10^\circ$$

the mean misorientation normalised to the LAGB/HAGB boundary.

External condition: the local burnup, entering *only* through the dislocation density

$$\rho_{\text{tot}}(bu) = 10^{2.2 \times 10^{-2} bu + 13.8}$$

Nogita & Une (1994)

Free energy

$$F(bu, \eta) = C_0 + C_2 \eta^2 + C_4 \eta^4$$

Only even powers: the energy cannot depend on the *sign* of a misorientation.

Minimising F gives Θ ; the same wall geometry gives r_n ; the lever rule gives X .

Three adjustable parameters

β (wall geometry), k (sweeping), ρ_c (strain-field cut-off).

The geometric wall

A low-angle boundary *is* a wall of dislocations.

1. Spacing sets the angle $\theta = b/d$

so a wall of n dislocation families carries a line length per unit *wall area*

$$L_A = n\theta/b$$

2. Wall area per unit volume or low angle grain boundary surface

$$S/V = 3\sqrt{\rho_{\text{LAGB}}} / \beta$$

β : the one geometric parameter (Rest & Hofman 2000).
 $n = 2$, Gourdet & Montheillet, not fitted (between 1-3).

Close the two on each other:

$$\rho_{\text{LAGB}} = L_A \cdot S/V$$

$$\Rightarrow \sqrt{\rho_{\text{LAGB}}} = \frac{3n\theta}{\beta b}$$

Everything follows from θ alone

$$\rho_{\text{LAGB}} = \left(\frac{3n\theta}{\beta b} \right)^2, \quad r_n \simeq \frac{\beta^2 b}{6n\theta}$$

The dislocation balance

Every dislocation is in exactly one of three states, and they must add up to ρ_{tot} :

$$\underbrace{\rho_{\text{ord}} = \rho_{\text{LAGB}}^{\text{max}} \eta^2}_{\text{condensed into low-angle walls}} + \underbrace{\rho_{\text{swept}} = (\rho_{\text{tot}} - \rho_{\text{ord}}) \frac{\Delta R}{R}}_{\text{annihilated by moving boundaries}} + \underbrace{\rho_{\text{free}}}_{\text{still a random array}} = \rho_{\text{tot}}$$

Each population carries the line energy of the state it is in:

$$F = \rho_{\text{free}} A_1 G b^2 + \rho_{\text{ord}} A_2 G b^2, \quad A_i = \frac{f(\nu)}{4\pi} \ln \frac{R_i}{b}$$

free ones screened at ρ_c , wall ones by the wall itself at ρ_{tot} ; the swept ones carry nothing.

The functional, collected

$$C_0 = \rho_{\text{tot}} A_1 G b^2, \quad C_4 = \rho_{\text{LAGB}}^{\max} \left. \frac{\Delta R}{R} \right|_{\max} A_1 G b^2$$

$$C_2 = \underbrace{\rho_{\text{LAGB}}^{\max} (A_2 - A_1) G b^2}_{\text{walls: the screening gain}} - \underbrace{\rho_{\text{tot}} \left. \frac{\Delta R}{R} \right|_{\max} A_1 G b^2}_{\text{sweep}}$$

The engine of the transition is $A_2 - A_1$. As burnup rises, ρ_{tot} rises, the screening length due to wall formation shrinks, A_2 falls below A_1 , and it becomes cheaper to store dislocations in walls than to leave them random.

Equilibrium

$$\frac{\partial F}{\partial \eta} = 0 \implies \eta^2 = -\frac{C_2}{2C_4}, \quad \text{clipped at 0}$$

$$\eta = 0 \text{ wherever } C_2 \geq 0.$$

Condition on the minimisation problem: dislocation balance

The walls cannot hold more dislocations than exist, so $\rho_{\text{ord}} \leq \rho_{\text{tot}}$. The equilibrium is the minimum of F on the **admissible interval**, not the free stationary point:

Eq. (7b) — admissibility

$$\eta_{\text{bal}} = \sqrt{\min\left(\frac{\rho_{\text{tot}}}{\rho_{\text{LAGB}}^{\text{max}}}, 1\right)}, \quad \eta_{\text{eq}} = \min\left(\sqrt{-\frac{C_2}{2C_4}}, \eta_{\text{bal}}\right)$$

Results

Calibration

Joint fit of β, k, ρ_c on Θ and the subgrain sizes, while the restructured fraction is *not* in the objective.


$$J = \frac{\langle \Delta \Theta^2 \rangle}{\text{var } \Theta} + w \frac{\langle \Delta r^2 \rangle}{\text{var } r}$$

n (not fitted)	2
β	33.547
k	0.04697
ρ_c	1.166e15 m ⁻²

The calibration results are summarized in the table below.

	RMSE / R^2
Θ ($N = 41$, calibrated)	1.7616° / 0.772
X ($N = 27$, <i>not</i> fitted)	0.2122 / 0.710
r_n ($N = 14$, calibrated)	0.0678 μm / 0.774
PIE fraction ($N = 8$, <i>out-of-sample</i>)	0.1461 / +0.433

Validation against both datasets



Against the three models SCIANTIX already had


Burnup [MWd/kgU] at which α_r first reaches:

threshold	1 KJMA	2 KJMA+ bu_{inc}	3 ρ_d	4 Landau
1 %	19.5	34.5	51.2	51.1
10 %	37.8	52.8	54.8	53.5
50 %	64.2	79.3	72.3	67.7
90 %	90.1	105.2	112.3	87.7
99 %	109.7	124.6	161.7	91.1

- At the onset, option 4 lands **within 0.1 MWd/kgU of option 3**.
- They part at the top: the lever rule **saturates** when Θ hits the 10° cap, whereas KJMA approaches 1 asymptotically. Option 4 is done by 91 MWd/kgU, option 3 not before 162.
- Option 4 spans the transition in **40 MWd/kgU** against 90 for option 1.

Model applied to SCIANTIX

Does the new formation model disturb the porosity model?



Largest deviation $+0.044$
absolute at
91.3 MWd/kgHM
(+36 %), exactly the
saturation burnup. Held

against option 2 in
test_U02HBS; all four
options end within **0.17 %**
of the same porosity.

Outlook: from a local
functional to a phase field

What a local functional cannot give -> phase-field models

Problems of the Landau-like local functional

- no spatial quantities;
- no kinetics: equilibrium is instantaneous.

family	property	application/ref
KWC	two fields (ϕ, θ), allows subgrain rotation; singular diffusion equations	Nucleation via subgrain coalescence, Muramatsu (2014)
MPF	One order parameter per grain; stable time increments; rotation ignored	Subgrain growth, Khajezade <i>et al.</i> (2024)
HMP	Removes nonphysical linear gradient term; handles inclination-dependent GB energy	Coupled Cosserat crystal plasticity, Tandogan <i>et al.</i> (2024), Ghiglione <i>et al.</i> (2024)
PFC	Atomic-resolution density field; diffusive timescales	Interface morphology development during solidification, Nit-tala (2025)

Nucleation is usually **seeded ad hoc** at a critical density or stress; spontaneous nucleation from lattice-curvature gradients is obtained when coupling KWC with Cosserat crystal plasticity (Ghiglione, 2024).

Muramatsu *et al.* (2014): a KWC phase field for recrystallization

The functional⁷ — two fields, ϕ and θ :

$$\mathcal{F} = \int_V \left[f(\phi) + \frac{\alpha^2}{2} |\nabla \phi|^2 + s g(\phi) |\nabla \theta| + \frac{\epsilon^2}{2} h(\phi) |\nabla \theta|^2 \right] dV$$

with $g(\phi) = h(\phi) = \phi^2$, relaxed by $\dot{\phi} = -M_\phi \delta \mathcal{F} / \delta \phi$ and $\dot{\theta} = -M_\theta \delta \mathcal{F} / \delta \theta$.

$\phi = 1$ inside a subgrain; θ is the **lattice orientation**.

The *singular* $|\nabla \theta|$ term gives a boundary an energy growing with misorientation.

The local part (Eq. 7, $f_m = 0$):

$$f(\phi; E_s) = a_{ub}(1 - p(\phi)) E_s + a_{wg} W_b q(\phi)$$

$$q(\phi) = \phi^2(1 - \phi)^2$$

$$p(\phi) = \phi^3(10 - 15\phi + 6\phi^2)$$

- q : the **double well**, original matrix against new grains; its height $a_{wg} W_b$ sets the boundary energy;
- p : is a sigmoid-like function where $p'(0) = p'(1) = 0$ therefore it *tilts* the well without moving its two minima;
- E_s : the **stored dislocation energy**, the only driving force, supplied from outside the model.

How the paper nucleates: a subgrain group enclosed by high-angle ($> 10^\circ$) boundaries is *selected* as a nucleus candidate and grows after an *incubation period* — the criterion is **imposed**, not produced by the free energy.


The prototype: the Landau model supplies the driving force

Keep $q(\phi)$ and $p(\phi)$ exactly as above, and replace the externally supplied E_s by what the Landau model:

$$f_{\text{Mur}}(\phi; E_s) = a_{ub}(1 - p(\phi))E_s + a_{wg}W_b q(\phi)$$

$$f_{\text{new}}(\phi; bu, T) = C_0(1 - p(\phi)\eta) + a_{wg}W_b q(\phi)$$

Both C_0 and η come from the same $\text{hbs_state}(bu, T)$ that produces Θ , r_n and X .



Left: Eq. (7) at three stored energies. Right: f_{new} below, at, and above the threshold.

Summary

- [1] L.D. Landau, *On the theory of phase transitions*, Zh. Eksp. Teor. Fiz. **7** (1937) 19; L.D. Landau, E.M. Lifshitz, *Statistical Physics*, Part 1, 3rd ed., §143.
- [2] A.N. Kolmogorov, Izv. Akad. Nauk SSSR, Ser. Mat. **1** (1937) 355–359.
- [3] W.A. Johnson, R.F. Mehl, Trans. AIME **135** (1939) 416–442.
- [4] M. Avrami, *J. Chem. Phys.* **7** (1939) 1103–1112; **8** (1940) 212–224; **9** (1941) 177–184.
- [5] J.W. Christian, *The Theory of Transformations in Metals and Alloys*, Part I, 3rd ed., Pergamon (2002), ch. 12, *Formal Theory of Transformation Kinetics*.
- [6] F.J. Humphreys, *A unified theory of recovery, recrystallization and grain growth, based on the stability and growth of cellular microstructures — I. The basic model*, *Acta Mater.* **45** (1997) 4231–4240.

- [7] F.J. Humphreys, G.S. Rohrer, A.D. Rollett, *Recrystallization and Related Annealing Phenomena*, 3rd ed., Elsevier (2017), ch. 6 (recovery) and ch. 10 (growth and stability of cellular microstructures).
- [8] S. Gourdet, F. Montheillet, *A model of continuous dynamic recrystallization*, *Acta Mater.* **51** (2003) 2685–2699. *n*, and the sweeping term
- [9] W.T. Read, W. Shockley, *Dislocation models of crystal grain boundaries*, *Phys. Rev.* **78** (1950) 275–289. $\theta = b/d$, and the wall energy
- [10] J.F. Nye, *Some geometrical relations in dislocated crystals*, *Acta Metall.* **1** (1953) 153–162.
- [11] G.S. Rohrer, *Grain boundary energy anisotropy: a review*, *J. Mater. Sci.* **46** (2011) 5881–5895.

- [12] J. Rest, G.L. Hofman, *An alternative explanation for evidence that xenon depletion, pore formation and grain subdivision begin at different local burnups*, *J. Nucl. Mater.* **277** (2000) 231–238. *the analogue of β*
- [13] R. Kobayashi, J.A. Warren, W.C. Carter, *A continuum model of grain boundaries*, *Physica D* **140** (2000) 141–150. *the (ϕ, θ) functional*
- [14] M. Muramatsu, Y. Aoyagi, Y. Tadano, K. Shizawa, *Phase-field simulation of static recrystallization considering nucleation from subgrains and nucleus growth with incubation period*, *Comput. Mater. Sci.* **87** (2014) 112–122.
- [15] L.-Q. Chen, *Phase-field models for microstructure evolution*, *Annu. Rev. Mater. Res.* **32** (2002) 113–140. *the general framework*

- [16] T. Takaki, A. Yamanaka, Y. Tomita, *Phase-field modeling and simulation of nucleation and growth of recrystallized grains*, *Mater. Sci. Forum* **558–559** (2007) 1195–1200. *KWC, subgrain rotation*
- [17] M. Muramatsu, Y. Tadano, K. Shizawa, *A phase-field simulation of nucleation from subgrain and grain growth in static recrystallization*, *Mater. Sci. Forum* **584–586** (2008) 1045–1050. *nucleation by coalescence*
- [18] A. Khajezade, W. Poole, M. Greenwood, M. Militzer, *Large-scale multi-phase-field simulation of 2D subgrain growth*, *Metals* **14** (2024) 584. *MPF, Read–Shockley*
- [19] I.T. Tandogan, M. Budnitzki, S. Sandfeld, *A multi-physics model for the evolution of grain microstructure*, *Int. J. Plast.* **180** (2024) 104201. *HMP orientation field*

- [20] I.T. Tandogan, M. Budnitzki, S. Sandfeld, *A multi-physics model for dislocation driven spontaneous grain nucleation and microstructure evolution in polycrystals*, *J. Mech. Phys. Solids* (2025) 106325.
- [21] F. Ghiglione, A. Ask, K. Ammar, B. Appolaire, S. Forest, *Cosserat-phase-field modeling of grain nucleation in plastically deformed single crystals*, *J. Mech. Phys. Solids* **188** (2024) 105628. *spontaneous nucleation*
- [22] L. Kong et al., *A study of strain-driven nucleation and extension of deformed grain: phase field crystal and continuum modeling*, *Materials* **11** (2018) 1805.
- [23] S. Nittala et al., *Interface morphology and dislocation-mediated processes during rapid solidification of thin films*, *Acta Mater.* (2025) 121581. *PFC subgrain boundaries*
- [24] T. Barani et al., *Modeling high burnup structure in oxide fuels. . . Part I: HBS formation*, *J. Nucl. Mater.* **539** (2020) 152296. *option 1*

- [25] T. Barani *et al.*, . . . *Part II: Porosity evolution*, *J. Nucl. Mater.* **563** (2022) 153627.
porosity options 2–3
- [26] S. Biswas, L.K. Aagesen, *Comput. Mater. Sci.* **258** (2025) 114052, Eq. 45. *option 2, bu_{inc}*
- [27] M.S. Veshchunov, V.E. Shestak, *Model for evolution of crystal defects in UO_2 under irradiation up to high burn-ups*, *J. Nucl. Mater.* **384** (2009) 12–18. *option 3, $\rho_d(bu, T)$*
- [28] G. Khvostov *et al.*, *Approaches to modeling of high burn-up structure. . . in the START-3 code*, WRFPM-2005, Kyoto.
- [29] K. Nogita, K. Une, *Radiation-induced microstructural change in high burnup UO_2 fuel pellets*, *Nucl. Instrum. Methods B* **91** (1994) 301–306. *Eq. (1), $\rho_{tot}(bu)$*
- [30] K. Nogita, K. Une, *Irradiation-induced recrystallization in high burnup UO_2 fuel*, *J. Nucl. Mater.* **226** (1995) 302–310.

- [31] Hj. Matzke, M. Kinoshita, *Polygonization and high burnup structure in nuclear fuels*, *J. Nucl. Mater.* **247** (1997) 108–115.
- [32] J. Spino *et al.*, *J. Nucl. Mater.* **354** (2006) 66–84. *porosity option 1, and the swelling data*
- [33] I. Zacharie-Aubrun *et al.*, *Restructuring in high burn-up UO₂ fuels: experimental characterization by electron backscattered diffraction*, *J. Appl. Phys.* **132** (2022) 195903. *28 of the 42 EBSD points*
- [34] C. Onofri *et al.*, *Experimental characterizations by EBSD and TEM of sub-grain boundaries and dislocations in low irradiated UO₂ fuels*, *J. Nucl. Mater.* **615** (2025) 155981. *the other 14*
- [35] NEA, *Recommendations on nuclear fuel properties*, NEA/NSC/R(2024)1 (2025), p. 124. *Eq. (2), G and ν*

- [36] D. Pizzocri *et al.*, *SCIANTIX: a new open source multi-scale code for fission gas behaviour modelling*, *J. Nucl. Mater.* **532** (2020) 152042.
- [37] G. Zullo *et al.*, *The SCIANTIX code for fission gas behaviour: status, upgrades, separate-effect validation and future developments*, *J. Nucl. Mater.* **587** (2023) 154744.

Backup — the equations

$$(1) \rho_{\text{tot}}(bu) = 10^{2.2 \times 10^{-2} bu + 13.8}$$

$$(2) G(T, P, x, q), \nu(T, P, x, q) \quad \text{NEA/NSC/R(2024)1 p. 124; } f(\nu) = \frac{1-\nu/2}{1-\nu}$$

$$(3) \rho_{\text{LAGB}}^{\text{max}} = \left(\frac{3n\theta_{\text{max}}}{\beta b} \right)^2, \quad (S/V)_{\text{max}} = \frac{9n\theta_{\text{max}}}{\beta^2 b}, \quad \left. \frac{\Delta R}{R} \right|_{\text{max}} = \frac{k \rho_{\text{LAGB}}^{\text{max}}}{\rho_{\text{tot}}}$$

$$(4) A_1 = \frac{f(\nu)}{4\pi} \ln \frac{\rho_{\text{c}}^{-1/2}}{b}, \quad A_2 = \frac{f(\nu)}{4\pi} \ln \frac{\rho_{\text{tot}}^{-1/2}}{b}$$

$$(5,6) F = \rho_{\text{free}} A_1 G b^2 + \rho_{\text{ord}} A_2 G b^2 = C_0 + C_2 \eta^2 + C_4 \eta^4$$

$$(7,7b) \eta_{\text{eq}} = \min(\sqrt{-C_2/2C_4}, \eta_{\text{bal}}), \quad \eta_{\text{bal}} = \sqrt{\min(\rho_{\text{tot}}/\rho_{\text{LAGB}}^{\text{max}}, 1)}$$

$$(8) \Theta = \min(\eta_{\text{eq}} \theta_{\text{max}} \cdot \frac{180}{\pi}, \theta_{\text{HAGB}})$$

$$(9) r_n = \min\left(\frac{1.5}{(S/V)}\left(1 + \frac{\Delta R}{R}\right), R_{\text{grain}}\right)$$

$$(10) X = \text{clip}\left(\frac{\Theta - \theta_{\text{u}}}{\theta_{\text{HAGB}} - \theta_{\text{u}}}, 0, 1 - 10^{-9}\right)$$

Backup — regimes and parameters

Regimes (T -, P -, x -independent)

condition	bu [GWd/tU]
$C_2 = 0$, Θ leaves 0	49.56
$\Theta = \theta_u$, X leaves 0	50.81
$\Theta = \theta_{\text{HAGB}}$	91.32


The balance bound sets η over roughly **65.6–91.3 GWd/tU**, and at 11 of the 41 EBSD points.

Fixed constants

b	3.889e-10 m
θ_{max}	$= \theta_{\text{HAGB}}$
θ_{HAGB}	10°
θ_u	1.00°
n	2


θ_u is the lower end member of the mixture Eq. (10) inverts, and it is set by the **measurement convention**, not fitted: the EBSD data reports a restructured fraction *at* 1° (f_1) and one *at* 10° (f_{10}), so 1° is the edge below which a boundary is not counted at all. A map whose whole resolved population sits there carries no restructuring — which is $X = 0$. It fixes only *where* X leaves zero: Θ and r_n do not depend on it.

Backup — the model on its own, $T = 600$ K, $P = 0.05$



```
python3 hbs_formation_landau.py --plot
```

Backup — the four regression cases, as they ship



Not the controlled comparison of the previous figure: each case pairs its formation option with the porosity model it was built around (1, 2, 3, 3), so part of the spread is the porosity model.

This is what a user of each regression case actually gets;
`formation_options.png` is what isolates the formation model.

Backup — the four formation options in a full run

HBS formation options on the same irradiation, porosity model 3 throughout

