

1.0 COMPOSITION

Styrene Butadiene Rubber (SBR) sheet compounded to remain soft and pliable.

2.0 USAGE

This gasketing material is particularly suitable for low pressure or saturated steam, hot or cold water, ammonia, and mild caustic soda up to temperatures of 180°F (82°C).

3.0 SPECIFIC PROPERTIES

- A. Thickness, Inches - 1/16, 3/32, 1/8, 3/16, 1/4
- B. Tensile Strength, PSI - 700 Minimum (48 BAR)
- C. Elongation, % - 200 Minimum
- D. Durometer - 65-85 Shore A
- E. Specific Gravity - 1.61 g/cc
- F. Compressibility - 50% maximum
- G. Width - 36" \pm 1" (90cm)
- H. Color - Red

A.W. CHESTERTON CO.

Middlesex Industrial Park, 225 Fallon Road
Stoneham, Massachusetts 02180-9101 USA
Telephone: 617-438-7000
Telex: 94-9417 • Fax: 617-438-8971
Cable: Chesterton Stoneham, Mass.
Web Address: <http://www.chesterton.com>

© A.W. CHESTERTON CO., 1997. All rights reserved.
® Registered trademark owned and licensed by
A.W. CHESTERTON CO. in USA and other countries.