LAB ALPHA - Tensile Test Certificate

ISO 6892-1, method B, room temperature

Specimen ID: AL-003

Material: Al 6061-T6

Test date: 2026-09-15

Yield strength (Rp0.2): 262 MPa

Tensile strength (Rm): 294 MPa

Elongation at break (A): 6.5 %

Remarks: Porosity visible on fracture surface, low ductility.