LAB ALPHA - Tensile Test Certificate

ISO 6892-1, method B, room temperature

Specimen ID: ST-101

Material: S355JR

Test date: 2026-09-23

Yield strength (Rp0.2): 381 MPa

Tensile strength (Rm): 528 MPa

Elongation at break (A): 26.0 %

Remarks: Resubmitted after re-test request.